

ECISS  
EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDISATION  
COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER  
EUROPÄISCHES KOMITEE FÜR EISEN-UND STAHLNORMUNG  
EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM – CRM)

**CERTIFICATE OF CHEMICAL ANALYSIS**  
**EURONORM – CRM No. 883-1, Blast furnace slag**

LABORATORY MEANS (4 values) - Mass content in %

Line No	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	Mo
1	0.9393	16.479	--	--	--	--	--	0.0029	1.0419	--	0.3668	--	0.0107	0.00048	<0.0003
2	0.9465	16.564	20.990	8.655	--	1.2783	0.5243	0.0030	1.0475	--	0.3683	0.1118	0.0112	0.00050	0.0003
3	0.9502	16.583	21.130	8.700	6.475	--	0.5278	0.0030	1.0483	0.2869	0.3750	0.1123	0.0113	0.00051	0.0003
4	0.9643	16.608	21.153	8.714	6.479	1.2918	0.5297	0.0030	1.0595	0.2902	0.3760	0.1155	0.0115	0.00052	0.0003
5	0.9676	16.625	--	8.741	6.488	1.2925	0.5310	0.0031	1.0600	0.2950	0.3766	0.1172	0.0116	0.00052	0.0003
6	0.9710	16.637	21.302	8.756	6.494	1.3109	0.5383	0.0031	1.0621	0.3001	0.3778	0.1174	0.0117	0.00053	0.0004
7	0.9738	16.641	21.313	8.863	6.503	1.3280	0.5383	0.0033	1.0728	0.3038	0.3894	0.1183	0.0118	0.00053	0.0004
8	0.9739	16.651	21.313	8.881	6.536	1.3320	0.5420	0.0033	1.0818	0.3180	0.3920	0.1206	0.0119	0.00055	0.0005
9	0.9774	16.663	21.314	8.908	6.545	1.3360	0.5434	0.0033	1.0838	0.3221	0.3923	0.1210	0.0121	0.00057	0.0005
10	0.9800	16.683	21.333	8.920	6.551	1.3433	0.5438	0.0038	1.1348	0.3223	0.3949	0.1215	0.0125	0.00058	<0.0008
11	0.9830	16.732	21.348	8.921	6.553	1.3458	0.5503	0.0038	1.1475	0.3223	0.3960	0.1218	0.0141	--	--
12	0.9875	16.763	21.366	8.935	6.554	1.3463	0.5507	0.0041	1.1528	0.3249	0.4008	0.1238	0.0143	--	--
13	0.9942	16.821	21.375	8.938	6.590	1.3470	0.5525	--	1.1575	0.3255	0.4009	0.1240	0.0146	--	--
14	0.9948	16.890	21.415	8.945	6.592	1.3510	0.5575	--	--	0.3272	0.4029	0.1243	0.0150	--	--
15	1.0041	--	21.489	8.991	6.620	1.3546	0.5578	--	--	0.3288	0.4070	--	0.0152	--	--
16	1.0043	--	21.678	9.041	6.703	1.3692	0.5669	--	--	0.3292	0.4100	0.1255	0.0153	--	--
17	1.0190	--	--	--	--	1.3700	0.5674	--	--	0.3296	0.4130	0.1287	0.0158	--	--
18	1.0450	--	--	--	--	--	0.5679	--	--	0.3299	0.4158	0.1337	--	--	--
19	--	--	--	--	--	--	--	--	--	--	0.4200	0.1344	--	--	--
20	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--
<b>M<sub>M</sub></b>	<b>0.9820</b>	<b>16.667</b>	<b>21.323</b>	<b>8.861</b>	<b>6.549</b>	<b>1.3331</b>	<b>0.5464</b>	<b>0.0033</b>	<b>1.0885</b>	<b>0.3160</b>	<b>0.3934</b>	<b>0.1219</b>	<b>0.0130</b>	<b>0.00053</b>	<b>≤0.001</b>
<b>S<sub>M</sub></b>	<b>0.0261</b>	<b>0.107</b>	<b>0.163</b>	<b>0.118</b>	<b>0.064</b>	<b>0.0280</b>	<b>0.0141</b>	<b>0.0004</b>	<b>0.0435</b>	<b>0.0153</b>	<b>0.0164</b>	<b>0.0065</b>	<b>0.0018</b>	<b>0.00004</b>	
<b>S<sub>W</sub></b>	<b>0.0119</b>	<b>0.155</b>	<b>0.152</b>	<b>0.053</b>	<b>0.079</b>	<b>0.0134</b>	<b>0.0058</b>	<b>0.0003</b>	<b>0.0147</b>	<b>0.0078</b>	<b>0.0080</b>	<b>0.0023</b>	<b>0.0008</b>	<b>0.00006</b>	

Line No	Ba	Sr	Zr	F	C	Zn	Pb	As	B	Ce	Li
1	--	--	--	--	0.100	0.0004	0.00004	0.00002	0.0050	0.0101	0.0035
2	0.0393	--	--	--	0.122	0.0004	<0.00005	0.00004	0.0051	--	0.0051
3	0.0395	0.0354	0.0230	<0.02	0.126	0.0005	0.00007	0.00007	0.0054	0.0131	0.0058
4	0.0398	0.0365	0.0241	0.0380	0.128	<0.0007	0.00010	0.00023	0.0058	0.0135	0.0060
5	0.0410	0.0368	0.0247	0.0393	0.135	0.0008	0.00020	<0.0005	0.0069	0.0135	0.0061
6	0.0435	0.0369	0.0268	0.0393	0.144	0.0008	<0.0005	<0.0007	0.0070	0.0145	0.0061
7	0.0446	0.0373	0.0272	--	0.146	0.0009	<0.0007	--	0.0078	0.0149	0.0066
8	0.0448	0.0373	0.0273	--	0.153	<0.0010	--	--	0.0079	0.0169	0.0077
9	0.0450	0.0375	0.0288	--	0.158	0.0012	--	--	--	--	--
10	0.0451	0.0388	0.0290	--	--	0.0012	--	--	--	--	--
11	0.0453	0.0388	0.0311	--	--	0.0015	--	--	--	--	--
12	0.0458	0.0391	0.0321	--	--	0.0019	--	--	--	--	--
13	0.0458	0.0393	0.0331	--	--	--	--	--	--	--	--
14	0.0476	0.0395	--	--	--	--	--	--	--	--	--
15	--	0.0403	--	--	--	--	--	--	--	--	--
<b>M<sub>M</sub></b>	<b>0.0436</b>	<b>0.0380</b>	<b>0.0276</b>								
<b>S<sub>M</sub></b>	<b>0.0028</b>	<b>0.0015</b>	<b>0.0034</b>								
<b>S<sub>W</sub></b>	<b>0.0017</b>	<b>0.0008</b>	<b>0.0011</b>								

M<sub>M</sub>: Mean of the intralaboratory means

S<sub>M</sub>: Standard deviation of the intralaboratory means

S<sub>W</sub>: Intralaboratory standard deviation

The laboratory mean values have been examined statistically to eliminate outlying values. Where a "----" appears in the table it indicates that an outlying value has been eliminated by either the Cochran or Grubbs Test. Values reported as "less than" by the participating laboratories have not been taken into account in the statistical calculations.

Additional values from laboratories for information (in µg/g)

Be: 0.0006; Bi: 0.000001; Cd: 0.00002; Co: 0.00006; Cs: 0.00003; Cu: 0.0001; Hf: 0.0008; Hg: 0.000001; Nb: 0.002; Rb: 0.001; Sb: 0.000002; Sc: 0.003; Se: 0.0004; Ta: 0.0001; Te: 0.000003; Th: 0.008; U: 0.001; W: 0.00002; Y: 0.006

**CERTIFIED VALUES - Mass content in %**

	Fe	Si	Ca	Mg	Al	Ti
<b>M<sub>M</sub></b>	<b>0.9820</b>	<b>16.67</b>	<b>21.32</b>	<b>8.86</b>	<b>6.55</b>	<b>1.3331</b>
<b>C(95 %)</b>	<b>0.0130</b>	<b>0.07</b>	<b>0.10</b>	<b>0.07</b>	<b>0.04</b>	<b>0.0155</b>
	Mn	P	S	Na	K	V
<b>M<sub>M</sub></b>	<b>0.546</b>	<b>0.0033</b>	<b>1.0885</b>	<b>0.316</b>	<b>0.393</b>	<b>0.122</b>
<b>C(95 %)</b>	<b>0.008</b>	<b>0.0003</b>	<b>0.0273</b>	<b>0.009</b>	<b>0.008</b>	<b>0.004</b>
	Cr	Ni	Mo	Ba	Sr	Zr
<b>M<sub>M</sub></b>	<b>0.0130</b>	<b>0.00053</b>	<b>≤0.001</b>	<b>0.0436</b>	<b>0.0380</b>	<b>0.0276</b>
<b>C(95 %)</b>	<b>0.0009</b>	<b>0.00003</b>		<b>0.0017</b>	<b>0.0009</b>	<b>0.0022</b>

The half-width confidence interval  $C(95\%) = \frac{t \times S_M}{\sqrt{n}}$  where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 sections 6.1 and 10.5.2

This certified reference material was prepared in accordance with the recommendations set out in ISO Guides 30 – 35 and issued by:

**swerea | KIMAB**

On behalf of: The Iron and Steel Nomenclature Co-ordinating Committee (COCOR) of the ECISS,  
after approval by all the participating laboratories and all the producing organisations.  
(France- ArcelorMittal Maizières/CTIF; Germany-Iron and Steel CRM Working Group: Stahlinstitut VDEh,  
BAM Bundesanstalt für Materialforschung und -prüfung & MPI für Eisenforschung;  
Nordic Countries-Nordic CRM Working Group)



JUNE 2015

**EURONORM – CRM No. 883-1**  
**METHODS USED**

Element	Line number	Methods
Fe	1.6.8.9.13.14.18 2.3.4.5.7.10.15.16 11 12 17	XRF ICP-OES ICP-MS FAAS Titration with Cr (VI) after reduction with Sn (II)
Si	1.3.7.10.11.12 2.5.6.8.9.14 4 13	XRF ICP-OES Gravimetry, dehydration with sulphuric acid Gravimetry, dehydration with perchloric acid
Ca	2.4.9.10.11.13 3.6.7.8.12.15.16 14	ICP-OES XRF Gravimetry after precipitation as oxalate
Mg	2.6.7.10.11.15 3.4.8.9.12.13.14.16 5	XRF ICP-OES Gravimetry, magnesium ammonium phosphate
Al	3.4.5.7.9.13.15 6.8.10.11.14.16 12	ICP-OES XRF FAAS, without separation
Ti	2.4.5.6.9.10.14.15.16 7.8.11.12.13.17	ICP-OES XRF
Mn	2.4.5.7.10.11.12.14.16.17 3.6.8.9.13 15 18	ICP-OES XRF FAAS ICP-MS
P	1.2.9.11 3.4.8 5.6.10 7.12	ICP-OES XRF ICP-MS MAS, phosphovanadomolybdate, extraction
S	1.4 2.3.7.8.10.11.12.13 5.6 9	Gravimetry as BaSO <sub>4</sub> without separation Combustion, infrared absorption ICP-OES XRF
Na	3.5.9.10.11.17.18 4.6.8.13.15.16 7.14 12	ICP-OES FAAS XRF ICP-MS
K	1.3.6.8.9.11.13 2.4.7.10.15.18 5.19 12.14.16.17	ICP-OES FAAS ICP-MS XRF
V	2.3.4.5.6.8.10.14.17.18.19 7 9.11.12.13.16	ICP-OES ICP-MS XRF
Cr	1.4.5.6.7.8.9.10.11.12.14.15.17 2 3.16 13	ICP-OES FAAS XRF ICP-MS
Ni	1.2.5.6.9 3.4.7.8.10	ICP-MS ICP-OES
Mo	1.5.8.9.10 2.3.4.6.7	ICP-OES ICP-MS
Ba	2.13 3.5.6.7.8.9.10.11.12 4.14	ICP-MS ICP-OES XRF
Sr	3.5.6.7.8.11.12.14 4.10.13.15 9	ICP-OES XRF ICP-MS
Zr	2.3.4.5.9.10.13 6.7.8 11.12	ICP-OES XRF ICP-MS
F	3 4.5 6	MAS, alizarin, pyrohydrolysis Ion chromatography Titration with Th (IV), visual end point, separation of interfering ions
C	1.2.3.4.5.8.9 6.7	Combustion, infrared absorption Combustion, non-aqueous titration after absorption in organic solvent
Zn	1.2.3.11 4.5.6.7.8 9.10.12	ICP-MS ICP-OES FAAS
Pb	1 2.3.4. 5.7 6	ETAAS ICP-MS ICP-OES FAAS
As	1 2.4 3 5.6	ETAAS ICP-MS MAS, diethyldithiocarbamate, separation as arsine ICP-OES
B	1.7.8 2.3.4 5.6	ICP-MS MAS, curcumin ICP-OES
Ce	1.3.5.6.8 4.7	ICP-OES ICP-MS
Li	1.2.3.5.7.8.9 4.6	ICP-OES ICP-MS

**Abbreviations:**

ETAAS	Electrothermal Atomic Absorption Spectrometry
FAAS	Flame Atomic Absorption Spectrometry
ICP-OES	Inductively Coupled Plasma – Optical Emission Spectrometry
ICP-MS	Inductively Coupled Plasma – Mass Spectrometry
MAS	Molecular Absorption Spectrophotometry
XRF	X-ray Fluorescence Spectrometry

## DESCRIPTION OF THE SAMPLE

The sample consists of powder that has been homogenised and sieved. From the material the fines passing a nominal 100 µm sieve have been removed. It is supplied in bottles containing 100 g.

## INTENDED USE & STABILITY

ECRM 883-1 is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where the calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the content should become discoloured (e.g. oxidised) due to atmospheric contamination it should be discarded.

## TRACEABILITY

**The traceability of ECRM 883-1 has been established in accordance with principles of ISO Guides 30 – 35 and the International vocabulary of basic and general terms in metrology.**

The assigned values for each material are achieved by inter-laboratory characterization, each laboratory using the method of their choice, details of which are given above. These methods are either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds. Most methods used were either international or national standard methods or methods which are technically equivalent.

## PARTICIPATING LABORATORIES

AG der Dillinger Hüttenwerke, Dillingen/Saar (Germany)  
 ALS Scandinavia AB, Luleå (Sweden)  
 A.M.C.O. united samplers and assayers GmbH, Duisburg (Germany)  
 AMG Superalloys UK Limited, Rotherham (UK)  
 ArcelorMittal Maizières Research SA, Maizières-lès-Metz (France)  
 ArcelorMittal, Dunkerque (France)  
 ArcelorMittal, Tubarão (Brazil)  
 BAM Bundesanstalt für Materialforschung und -prüfung, Berlin (Germany)  
 Chemad GmbH, Duisburg (Germany)  
 FEhS – Institut für Baustoff-Forschung, Duisburg (Germany)  
 GFE Fremat GmbH, Freiberg (Germany)  
 Industeel France - Le Creusot, Le Creusot (France)  
 Lucideon, Stoke-on-Trent (UK)  
 Muldenhütten Recycling und Umwelttechnik GmbH, Freiberg (Germany)  
 Ovako Sweden AB, Hofors (Sweden)  
 Pattinson & Stead (2005) Ltd., Middlesbrough (UK)  
 Ridsdale & Co. Ltd., Middlesbrough (UK)  
 SSAB Europe Oy, Raahе (Finland)  
 SSAB Special Steels, Oxelösund (Sweden)  
 Swerea KIMAB AB, Kista (Sweden)  
 ThyssenKrupp Steel Europe AG, Duisburg (Germany)  
 Umicore Precious Metals, Hoboken (Belgium)  
 voestalpine Stahl GmbH, Linz (Austria)  
 Weser-Metall GmbH, Nordenham (Germany)

## FURTHER INFORMATION

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMs) and the use of the statistical information given on this certificate, please refer either to the producer of this Certified Reference Material or to Technical Reports CEN/TR 10317:2014 and CEN/TR 10350:2013, both of which are available from the national standards body in your country. (In the UK this is the BSI, 389 Chiswick High Road, London W4 4AL). Further information and advice on this or other Certified Reference Materials or Reference Materials produced by Swerea KIMAB AB, may be obtained from the address below.

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Europäischen Zertifizierten Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendungen der in diesem Zertifikat enthaltenen statistischen Daten sind erhältlich beim Hersteller dieses zertifizierten Referenzmaterials, dessen Adresse auf diesem Zertifikat angegeben ist oder sie finden sich in den CEN-Reports CEN/TR 10317:2014 und CEN/TR 10350:2013, beide zu beziehen durch die nationalen Normenorganisationen (in Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstraße 4-10, 10787 Berlin). Weitere Informationen und Hinweise zu diesem oder anderen durch Swerea KIMAB AB hergestellten zertifizierten Referenzmaterialien oder Referenzmaterialien können unter der unten angegebenen Adresse erhalten werden.

Pour disposer d'informations sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM-MRC) ainsi que sur l'utilisation des informations statistiques données sur ce certificat, se reporter soit au producteur de ce Matériau de Référence Certifié, soit aux Rapports Techniques CEN/TR 10317:2014 et CEN/TR 10350:2013. On peut se procurer ces deux documents auprès des organismes nationaux de normalisation. (Pour la France: AFNOR, 11 Avenue Francis de Pressensé, 93571 – St Denis la Plaine Cedex).

D'autres informations et avis au sujet de ce Matériau de Référence Certifié, ou de tout autre Matériau de Référence Certifié ou Matériau de Référence produit par le Swerea KIMAB AB, peuvent être demandés en contactant l'adresse figurant dans le bas de ce Certificat.

För information angående tillverkning, certifiering och anskaffning av dessa europeiska certifierade referensmaterial (EURONORM CRM) och för användning av statistisk information, som angivits i detta certifikat, refereras antingen till producenten av detta certifierade referensmaterial eller till Teknisk Rapport CEN/TR 10317:2014 och CEN/TR 10350:2013 som kan erhållas från den nationella standardiseringsorganisationen. (Sverige: SIS, S:t Paulsgatan 6, SE-118 80 Stockholm, Finland: SFS, PL. 116, FIN-002 41, Helsingfors, Danmark: DS, Kollegievej 6, DK-Charlottenlund 2920, Norge: NSF, Drammensveien, 145 A, Postboks 353 Skøyen, NO-0213 Oslo, Island: STRI, Holtagardar, IS-104 Reykjavik).

Ytterligare information och rådfrågan om detta eller andra Certifierade Referensmaterial/Referensmaterial, producerade av Swerea KIMAB AB, kan erhållas från angiven adress enligt nedan.

Karin Ingelgård/Michael Granfors  
Responsible for CRM certification