

---

**Approximate composition of SUS – SnSUS6, high alloy, Sn base**  
**Sample size approx. 40 mm dia. x 30 mm thickness**

**Composition:**  
**Description in %**

<b>Tin .....</b>	<b>Balance</b>	<b>Copper .....</b>	<b>0.14</b>
<b>Lead .....</b>	<b>1.42</b>	<b>Gold .....</b>	<b>0.02</b>
<b>Antimony .....</b>	<b>0.49</b>	<b>Iron .....</b>	<b>0.02</b>
<b>Arsenic .....</b>	<b>0.27</b>	<b>Nickel .....</b>	<b>0.04</b>
<b>Bismuth .....</b>	<b>0.09</b>	<b>Cobalt .....</b>	<b>0.02</b>
<b>Cadmium .....</b>	<b>0.02</b>	<b>Tellurium .....</b>	<b>(0.05)</b>
<b>Indium .....</b>	<b>0.06</b>		
<b>Thallium .....</b>	<b>(0.005)</b>		
<b>Silver .....</b>	<b>0.12</b>		