


SET OF RMS OF THE FIRECLAYS
No's 137, 138, 139

| | %SiO ₂ | %Al ₂ O ₃ | %Fe ₂ O ₃ | %TiO ₂ | %MgO | %CaO | %Na ₂ O | %K ₂ O | %LOI |
|-----|-------------------|---------------------------------|---------------------------------|-------------------|------|------|--------------------|-------------------|------|
| 137 | 61,46 | 32,43 | 1,63 | 1,13 | 0,28 | 0,28 | 0,126 | 1,31 | 1,24 |
| 138 | 68,90 | 26,01 | 1,47 | 0,92 | 0,22 | 0,25 | 0,10 | 0,98 | 0,92 |
| 139 | 82,41 | 13,80 | 0,84 | 0,53 | 0,12 | 0,14 | 0,059 | 0,51 | 0,78 |

The confidence interval is expressed by the last valid figure according to the 4.6.3. of ISO REMCO GUIDE 35/85 (E).

Producer:
Mittal Steel Ostrava Corp.
Ostrava
CZECH REPUBLIC

Ing. Petr Šuchma
Head of the Metallurgical and Chemical Laboratories
Mittal Steel Ostrava Corp.



MITTAL
Mittal Steel Ostrava a.s.
Vratimovská 689, 707 02 Ostrava-Kunčice
Hutní a chemické laboratoře