

United States Geological Survey

Certificate of Analysis



Labmix24 GmbH
Industriestr. 18 A
46499 Hamminkeln
Germany
Tel. +49 2852 96064-00
Info@labmix24.com
www.labmix24.com

Green River Shale, SGR-1b

Sample for this reference material was collected from the Mahogany zone of the Green River Formation. It is a petroleum and carbonate-rich shale. At the time of preparation, shale oil tests yield 51 to 57 gallons per ton.

Element concentrations were determined by cooperating laboratories using a variety of analytical methods. Certificate values are based primarily on international data compilations (Abbey, 1983, Gladney and Roelandts, 1988, Govindaraju, 1994). Initial USGS studies (Flanagan, 1976) provide limited background information on this reference material.

Compilation values

Oxide	Wt %	s.d.	Oxide	Wt %	s.d.
SiO ₂	28.24	0.21	CaO	8.38	0.17
Al ₂ O ₃	6.52	0.21	MgO	4.44	0.20
K ₂ O	1.66	0.10	P ₂ O ₅	0.328	0.066
Na ₂ O	2.99	0.13	TiO ₂	0.253	0.025
Fe ₂ O ₃ T	3.03	0.14	S _{tot}	1.53	0.11

Element	µg/g	s.d.	Element	µg/g	s.d.	Element	µg/g	s.d.
As	67	5	Eu	0.56	0.09	Sb	3.4	0.5
B	54	3	F	1960	240	Sc	4.6	0.7
Ba	290	40	Hf	1.4	0.14	Sm	2.7	0.3
Ce	36	4	La	20	1.8	Sr	420	30
Co	12	1.5	Li	147	26	Th	4.8	0.21
Cr	30	3	Mn	267	34	U	5.4	0.4
Cs	5.2	0.3	Mo	35	0.9	V	130	6
Cu	66	9	Nd	16	1.7	W	2.6	0.06
Er	1.1	0.14	Pb	38	4	Zn	74	9

Oxide	Wt %	Oxide	Wt %
Fe ₂ O ₃	1.46	FeO	1.41
C _{tot}	28	C _{inorg}	3.2

Element	µg/g	Element	µg/g	Element	µg/g
Cd	0.9	Ho	0.4	Sn	1.9
Cl	32	Li	147	Tm	0.17
Dy	1.9	Nb	5.2	Y	13
Ga	12	Ni	29	Yb	0.94
Gd	2	Se	3.5	Zr	53
Hg	0.3				

Denver, Colorado
revised August 2001

Dr. Stephen Wilson
Reference Material Project
CICT

Bibliography

Abbey, S., 1983, Studies in "Standard Samples" of Silicate Rocks and Minerals 1969-1982, Canadian Geological Survey paper 83-15, p-114.

Flanagan, F.J., 1976, Descriptions and Analyses of Eight New USGS Rock Standards, U.S. Geological Survey Professional Paper 840, p 192

Gladney E.S., and Roelandts, I., 1988, 1987 Compilation of Elemental Concentration Data for USGS BHVO-1, MAG-1, QLO-1, RGM-1, SCo-1, SDC-1, SGR-1, and STM-1, Geostandards Newsletter, 12: 253-362.

Govindaraju, K., 1994, 1994 Compilation of Working Values and Descriptions for 383 Geostandards, Geostandards Newsletter, 18:1-158

Glossary

Fe ₂ O ₃ T	Total iron expressed as Fe ₂ O ₃
C _{tot}	Total carbon concentration
C _{inorg}	Inorganic carbon concentration
S _{tot}	Total sulfur concentration
Wt %	Percent of total element concentration
µg/g	Total element concentration expressed as micrograms of element per gram of solid sample
s.d.	One standard deviation

Notes

Unless otherwise indicated total element concentrations are reported for material on an as-received basis, i.e. no drying.

Samples may be obtained from the U.S. Geological Survey through the Reference Materials Project, Stephen Wilson coordinator. Request for standards should be forwarded to the following address

Dr. Stephen Wilson
U.S. Geological Survey
Reference Materials Project
PO Box 25046 MS 973
Denver, Co. 80225