



# CZECH METROLOGY INSTITUTE

AUTHORIZED REFERENCE MATERIALS CERTIFYING BODY, PRAGUE

V Botanice 4, CZ-150 72 Praha 5, tel: +420 2 5732 4096, fax: +420 2 5732 4982

## CERTIFICATE

### SET OF CERTIFIED REFERENCE MATERIALS CZ 2002 LOW ALLOY CAST IRON FOR SOLID SAMPLE SPECTROMETRY CRM 241 - 249 A-D

**Designed** for the calibration and validation of methods of spectrometrical analysis on the planes of solid samples with an analyzed area of at least 4 mm in diameter: Atomic Emission Spectrometry with spark, glow discharge or laser excitation and X-ray Fluorescence Spectrometry.

The CRMs can be used as a set of nine or as individual samples.

**Manufacture and Technical Parameters.** The samples were chill-cast white on a massive copper block with controlled speed at a controlled temperature of the molten metal.

The samples are truncated pyramids with a base analytical surface (38x38 mm), a minimum total height of 20 mm and a side ledge 11-13 mm high. The samples can be used till 1 mm of the ledge height remains. The certified portion of a sample thus extends 10-12 mm from the original analytical surface.

The samples are electro-spark marked on surfaces opposite to the analytical surfaces.

Shrinkage cavities and porosity which may appear in the uncertified portions of the samples due to the applied technology and the properties of the material do not affect the analytical performance of the certified portions.

**Homogeneity** was tested by Atomic Emission Spectrometry with an analytical area approximately 4 mm in diameter.

Tested were the random homogeneity and the trend homogeneity along the height of the certified portion and the trend homogeneity of the casting sequence. The latter test was supported by Combustion - IR Molecular Absorption Spectrometry and Thermoevolution.

#### Producer

ČKD Technical Laboratories, Na Harfě 9, CZ - 190 02 Praha, Czech Republic

Fax: + 420 2 66036578, E-mail: techlab@anet.cz

**Project Manager:** Miroslav Gorný

Quality Management System ISO 9001 is in force with the producer. Production, testing and certification were carried out in compliance with the ISO-REMCO Guide 34 (2000).

**Certificate No.:** 017/CR/045

**Date of Issue:** 21.3. 2000

**Valid until:** 21.3.2015

Pavel Klenovský  
CMI Director



## CERTIFICATION

**Principle and Traceability.** Certification based on an interlaboratory experiment performed by various independent analytical methods was carried out in compliance with the ISO-REMCO Guide 35 ( 1989 ).

The results were traced to the former 241 through 249 CRM set and standard primary substances. The methods were validated by matrix-matching CRMs.

**Methods.** Atomic Emission Spectrometry with spark and glow discharge excitation and X-ray Fluorescence Spectrometry were applied on a plane of the solid sample. Crushed certified portions of the samples were analyzed by Combustion - IR Molecular Absorption Spectrometry, Thermoevolution, Instrumental Neutron Activation Analysis and by solution methods which comprised Atomic Emission Spectrometry with Inductively Coupled Plasma excitation directly and with hydrides generation, Flame and Electro-Thermal Atomization Atomic Absorption Spectrometry, Molecular Absorption Spectrometry ( Spectrophotometry ) and Gravimetry.

### Participating laboratories:

Analytical Laboratories Plzeň, Plzeň  
ARL, Ecublens, Switzerland  
ČKD Technical Laboratories, Praha  
LECO Instrumente Plzeň, Plzeň  
Nová huť, Ostrava  
Nuclear Physics Institute, Řež u Prahy  
Pramet Tools, Šumperk

Škoda, Plzeň  
Škoda Auto, Mladá Boleslav  
Třinecké železářny, Třinec  
Vítkovice, Ostrava  
ŽDAS, Žďár nad Sázavou  
Železářny a drátovny Bohumín, Bohumín  
Železářny Hrádek, Hrádek u Rokycan

**Evaluation.** First the values of laboratory means were assessed technically to justify the deletion of possible outliers. Next the normal distribution of the laboratory means in each set was verified and the unrounded arithmetic averages and their standard deviations calculated.

**Certified values** are the averages of at least six accepted laboratory means the normal distributions of which were not rejected, rounded identically as their stated uncertainties.

**Uncertainty** was estimated with respect to ISO Guide to the Expression of Uncertainty in Measurement ( 1993 ) and Document EURACHEM, 1995 - Quantifying Uncertainty in Analytical Measurement as an expanded combined uncertainty. It is expressed as the  $\pm$  half-width interval except for certified zero values for which only the + halfwidth interval applies. The sources of the estimates of uncertainty were the standard deviation of an average of the laboratory means and a contribution of the combined inhomogeneities when found to be statistically significant. A coverage factor of 2,3 was applied.

The uncertainty statement is given by two significant figures at most and holds only for analytical areas 4 mm or more in diameter.

**Uncertified values** are given when less than six accepted laboratory means were available and serve only as supplementary matrix information. They must not be used for calibration and validation.

**Stability and storage.** The CRM materials and certified constituents are stable over the entire period of validity. The samples must be stored in a non-corrosive environment.

**Users instructions.** The analytical surfaces of the CRMs must be prepared prior to analysis in the same way as the analyzed samples in agreement with the Instrument Operation Instructions.



SET OF LOW ALLOY CAST IRON SPECTROMETRIC CERTIFIED REFERENCE MATERIALS CZ 2002

NINE TYPES 241 - 249A, B, C, D

N°	% m/m	C	Mn	Si	P	S	Ni	Cr	Cu	Mo	V	Ti	Al	Mg	Ce	B	N°
241B	value U <sub>c</sub>	1,84 0,02	0,060 0,002	3,15 0,03	0,007 0,001	0,123 0,005	0,021 0,001	0,683 0,005	0,011 0,001	0,61 0,01	0,080 0,002	0,001 0,001	0,003 0,001	0,000 0,0005	0,000 0,0006	0,001	241B
242B	value U <sub>c</sub>	2,06 0,02	0,189 0,004	2,81 0,03	0,044 0,001	0,028 0,002	0,022 0,001	0,031 0,001	0,040 0,002	1,21 0,01	0,46 0,01	0,28 0,01	0,042 0,002	0,000 0,0005	0,00	0,005 0,001	242B
242A	value U <sub>c</sub>	1,84 0,02	0,060 0,002	3,06 0,03	0,039 0,001	0,036 0,002	0,039 0,001	0,029 0,001	0,055 0,002	1,13 0,01	0,37 0,01	0,19 0,01	0,036 0,003	0,000 0,0005	0,00	0,008 0,001	242A
243A	value U <sub>c</sub>	2,32 0,03	0,422 0,007	2,39 0,02	0,173 0,005	0,082 0,002	0,085 0,002	0,398 0,005	0,187 0,002	0,262 0,004	0,154 0,005	0,023 0,002	0,013 0,002	0,000 0,0005	0,000 0,001	0,009 0,001	243A
244B	value U <sub>c</sub>	2,57 0,03	0,68 0,01	2,06 0,03	0,022 0,001	0,011 0,001	0,336 0,003	0,360 0,003	0,308 0,003	0,056 0,001	0,002 0,001	0,019 0,001	0,019 0,002	0,025 0,001	0,018 0,003	0,093 0,003	244B
245B	value U <sub>c</sub>	2,95 0,03	1,38 0,01	1,59 0,02	0,42 0,01	0,035 0,002	0,194 0,002	0,197 0,003	0,081 0,002	0,115 0,002	0,055 0,002	0,110 0,002	0,038 0,002	0,003 0,001	0,00	0,003 0,001	245B
245A	value U <sub>c</sub>	2,94 0,03	1,38 0,01	1,58 0,02	0,41 0,01	0,039 0,002	0,161 0,003	0,166 0,004	0,076 0,003	0,114 0,002	0,073 0,002	0,087 0,003	0,019 0,002	0,003 0,001	0,00	0,007 0,001	245A
246B	value U <sub>c</sub>	2,73 0,03	0,354 0,005	0,76 0,01	0,66 0,01	0,020 0,002	0,065 0,001	1,16 0,01	1,39 0,01	0,009 0,001	0,013 0,001	0,014 0,001	0,101 0,005	0,016 0,001	0,007 0,002	0,000 0,0005	246B
247B	value U <sub>c</sub>	3,09 0,04	1,05 0,01	1,20 0,02	0,098 0,003	0,0034 0,0009	0,437 0,003	0,041 0,001	0,822 0,004	0,023 0,001	0,013 0,001	0,067 0,002	0,043 0,002	0,056 0,003	0,053 0,003	0,000 0,0005	247B
248B	value U <sub>c</sub>	3,34 0,02	0,265 0,003	1,82 0,02	0,050 0,001	0,0033 0,0005	0,680 0,007	0,022 0,001	0,124 0,002	0,001 0,001	0,142 0,003	0,163 0,003	0,026 0,002	0,037 0,002	0,030 0,002	0,039 0,002	248B
248C	value U <sub>c</sub>	3,39 0,02	0,281 0,002	1,78 0,02	0,053 0,001	0,0035 0,0005	0,688 0,007	0,052 0,001	0,132 0,002	0,001 0,001	0,162 0,003	0,133 0,003	0,028 0,002	0,048 0,002	0,036 0,002	0,038 0,002	248C
249B	value U <sub>c</sub>	4,06 0,03	0,121 0,002	0,47 0,01	0,26 0,01	0,0078 0,0007	1,16 0,02	0,102 0,001	0,474 0,008	0,013 0,001	0,019 0,002	0,046 0,002	0,105 0,006	0,040 0,002	0,021 0,002	0,016 0,001	249B
249C	value U <sub>c</sub>	4,06 0,03	0,099 0,002	0,49 0,01	0,27 0,01	0,0075 0,0007	1,21 0,02	0,148 0,002	0,486 0,005	0,011 0,001	0,026 0,002	0,026 0,002	0,032 0,002	0,042 0,002	0,017 0,002	0,017 0,001	249C
249D	value U <sub>c</sub>	3,76 0,03	0,127 0,002	0,34 0,01	0,25 0,01	0,008 0,001	1,42 0,02	0,093 0,001	0,479 0,007	0,013 0,001	0,023 0,002	0,095 0,002	0,056 0,002	0,051 0,002	0,08	0,018 0,001	249D
249A	value U <sub>c</sub>	4,10 0,03	0,197 0,003	0,91 0,02	0,26 0,01	0,013 0,001	1,20 0,02	0,083 0,002	0,497 0,005	0,010 0,001	0,032 0,003	0,084 0,003	0,047 0,003	0,067 0,003	0,027 0,003	0,015 0,002	249A

*Handwritten signature*



N°	% m/m	Sn	Sb	As	Pb	Bi	Zn	Se	Te	Co	W	Nb	Zr	La	N	Fe	N°
241B	value U <sub>c</sub>	0,003	<b>0,139</b> 0,006	<b>0,002</b> 0,001	<b>0,001</b> 0,001	<b>0,000</b> 0,001	<b>0,000</b> 0,0005	0,00	0,000	<b>0,004</b> 0,001	<b>0,001</b> 0,001	<b>0,003</b> 0,001	<b>0,000</b> 0,0005	<b>0,000</b> 0,0005	<b>0,0053</b> 0,0004	93,2	241B
242B	value U <sub>c</sub>	0,010 0,002	<b>0,005</b> 0,001	<b>0,009</b> 0,001	<b>0,027</b> 0,002	<b>0,020</b> 0,002	0,00	0,002	0,031	<b>0,004</b> 0,001	0,002	<b>0,009</b> 0,001	0,000	<b>0,000</b> 0,0005	<b>0,0092</b> 0,0005	92,6	242B
242A	value U <sub>c</sub>	0,010 0,002	<b>0,007</b> 0,001	<b>0,015</b> 0,001	0,012	0,015	0,00	0,000	0,08	<b>0,002</b> 0,001	0,007	<b>0,013</b> 0,001	0,000	0,00		92,9	242A
243A	value U <sub>c</sub>	0,114 0,003	<b>0,086</b> 0,002	<b>0,087</b> 0,004	0,055	0,001	<b>0,018</b> 0,001	0,055	0,000	<b>0,026</b> 0,001	<b>0,029</b> 0,002	<b>0,019</b> 0,001	<b>0,000</b> 0,0005	<b>0,000</b> 0,0005	<b>0,0037</b> 0,0003	93,0	243A
244B	value U <sub>c</sub>	0,179 0,003	<b>0,004</b> 0,001	<b>0,040</b> 0,001	<b>0,002</b> 0,001	<b>0,000</b> 0,0005	<b>0,026</b> 0,002	0,000	0,000	<b>0,049</b> 0,002	<b>0,052</b> 0,002	<b>0,006</b> 0,001	<b>0,025</b> 0,001	<b>0,009</b> 0,001		93,0	244B
245B	value U <sub>c</sub>	0,076 0,002	<b>0,052</b> 0,002	<b>0,006</b> 0,001	<b>0,020</b> 0,002	<b>0,009</b> 0,001	0,00	0,029	0,017	<b>0,007</b> 0,001	<b>0,020</b> 0,002	<b>0,029</b> 0,001	<b>0,004</b> 0,001	0,00		92,5	245B
245A	value U <sub>c</sub>	0,076 0,003	<b>0,050</b> 0,002	<b>0,002</b> 0,001	<b>0,015</b> 0,001	<b>0,008</b> 0,001	<b>0,000</b> 0,0005	0,036	0,018	<b>0,003</b> 0,001	<b>0,021</b> 0,003	0,001	<b>0,003</b> 0,001	0,00		92,7	245A
246B	value U <sub>c</sub>	0,002 0,001	<b>0,004</b> 0,001	<b>0,003</b> 0,001	0,002	0,001	0,00	0,00	0,00	<b>0,012</b> 0,001	0,011	0,001	<b>0,000</b> 0,0005	<b>0,003</b> 0,001		92,6	246B
247B	value U <sub>c</sub>	0,038 0,001	<b>0,005</b> 0,001	<b>0,010</b> 0,001	0,002	<b>0,007</b> 0,001	<b>0,012</b> 0,001	0,000	0,008	<b>0,095</b> 0,003	0,002	<b>0,052</b> 0,001	<b>0,009</b> 0,001	<b>0,019</b> 0,002		92,7	247B
248B	value U <sub>c</sub>	0,017 0,001	<b>0,017</b> 0,001	<b>0,018</b> 0,001	<b>0,013</b> 0,001	<b>0,002</b> 0,001	<b>0,009</b> 0,001	0,005	0,002	<b>0,014</b> 0,001	<b>0,001</b> 0,001	<b>0,005</b> 0,001	<b>0,013</b> 0,001	<b>0,009</b> 0,001		93,1	248B
248C	value U <sub>c</sub>	0,016 0,001	<b>0,017</b> 0,001	<b>0,019</b> 0,001	<b>0,013</b> 0,001	<b>0,002</b> 0,001	<b>0,008</b> 0,001	0,007	0,003	<b>0,013</b> 0,001	<b>0,001</b> 0,001	<b>0,003</b> 0,001	<b>0,012</b> 0,001	<b>0,011</b> 0,001		93,0	248C
249B	value U <sub>c</sub>	0,007 0,001	<b>0,005</b> 0,001	<b>0,017</b> 0,001	<b>0,013</b> 0,001	<b>0,006</b> 0,001	<b>0,006</b> 0,001	0,005	0,00	<b>0,013</b> 0,001	0,011	<b>0,013</b> 0,001	<b>0,048</b> 0,001	<b>0,006</b> 0,002		92,9	249B
249C	value U <sub>c</sub>	0,002 0,001	<b>0,005</b> 0,001	<b>0,016</b> 0,001	<b>0,009</b> 0,001	<b>0,004</b> 0,001	<b>0,006</b> 0,001	0,002	0,00	<b>0,014</b> 0,001	<b>0,009</b> 0,001	<b>0,011</b> 0,001	<b>0,027</b> 0,001	<b>0,004</b> 0,001		92,9	249C
249D	value U <sub>c</sub>	0,004 0,001	<b>0,004</b> 0,001	<b>0,018</b> 0,001	<b>0,025</b> 0,002	0,006	<b>0,004</b> 0,001	0,003	0,002	<b>0,011</b> 0,001	0,01	<b>0,035</b> 0,001	<b>0,039</b> 0,001	0,023		93,0	249D
249A	value U <sub>c</sub>	0,003 0,001	<b>0,002</b> 0,001	<b>0,014</b> 0,002	<b>0,015</b> 0,002	<b>0,007</b> 0,001	<b>0,004</b> 0,001	0,005	0,00	<b>0,020</b> 0,002	0,01	<b>0,021</b> 0,002	<b>0,028</b> 0,002	<b>0,007</b> 0,002		92,3	249A

CERTIFICATE No.: 017/CR/045 p.3 for the certifying body:

Certified values: bold figures with uncertainty statement

Uncertified values: thin figures without uncertainty statement. For information only, they must not be used for validation or calibration.

Uncertainties: U<sub>c</sub>, expanded combined uncertainty as the  $\pm$  halfwidth interval except for certified zero values for which the + interval applies.

*Trig*