

**ECIIS**  
**EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDISATION**  
**COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER**  
**EUROPÄISCHES KOMITEE FÜR EISEN-UND STAHLNORMUNG**

EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM – CRM)

CERTIFICATE OF CHEMICAL ANALYSIS

**EURONORM – CRM No. 269-1, HIGH ALLOY STEEL**

LABORATORY MEANS (4 values) - Mass content in %

Line No	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	Nb
1	0.0473	---	1.2285	0.0295	0.0006	---	0.3806	---	0.0056	---	0.3505	0.0421	0.0211
2	0.0486	0.4270	---	0.0295	0.0007	0.3868	7.975	0.0056	---	0.3563	0.0447	0.0220	
3	0.0489	0.4279	1.2456	0.0296	0.0008	18.048	0.3871	7.988	0.0056	0.1072	0.3563	0.0449	0.0227
4	0.0490	0.4293	1.2466	0.0298	0.0008	18.080	0.3882	7.996	0.0058	0.1079	0.3597	0.0451	0.0236
5	0.0490	0.4317	1.2475	0.0303	0.0009	18.091	0.3889	8.003	0.0058	0.1088	0.3614	0.0451	0.0236
6	0.0493	0.4346	1.2520	0.0305	0.0009	18.105	0.3934	8.025	0.0060	0.1094	0.3624	0.0451	0.0239
7	0.0497	0.4348	1.2542	0.0308	0.0010	18.128	0.3942	8.035	0.0060	0.1103	0.3630	0.0451	0.0240
8	0.0498	0.4353	1.2563	0.0309	0.0011	18.128	0.3946	8.037	0.0061	0.1112	0.3634	0.0459	0.0241
9	0.0498	0.4386	1.2578	0.0311	0.0011	18.130	0.3962	8.037	0.0061	0.1119	0.3642	0.0460	0.0241
10	0.0499	0.4387	1.2605	0.0313	0.0011	18.133	0.3963	8.043	0.0062	0.1121	0.3642	0.0466	0.0242
11	0.0501	0.4418	1.2617	0.0313	0.0012	18.149	0.3967	8.050	0.0062	0.1124	0.3666	0.0471	0.0245
12	0.0517	0.4420	1.2627	0.0315	0.0013	18.150	0.3970	8.054	0.0063	0.1124	0.3669	0.0479	---
13	0.0526	0.4446	1.2640	0.0315	0.0014	18.159	0.3970	8.056	0.0064	0.1126	0.3680	0.0482	0.0250
14	0.0527	0.4450	1.2650	0.0315	0.0014	18.195	0.3991	8.063	0.0064	0.1129	0.3683	0.0497	0.0254
15		0.4456	1.2650	0.0316		18.202	0.4021	8.064	0.0064	0.1129	0.3694		0.0257
16		0.4462	1.2785	0.0321		18.203	0.4033	8.068	0.0068	0.1130	0.3698		0.0258
17		0.4464	1.2800	0.0324		18.211	0.4049	8.073	0.0068	0.1133	0.3698		0.0274
18		0.4486	1.2913	0.0326		18.212	0.4060	8.100		0.1134	0.3715		
19		0.4498	1.2946	0.0336		18.219	0.4082	8.131		0.1156	0.3730		
20		0.4505		0.0343		0.4083					0.3742		
21		0.4573				0.4103					0.3759		
<b>M<sub>M</sub></b>	<b>0.0499</b>	<b>0.4408</b>	<b>1.2618</b>	<b>0.0313</b>	<b>0.0010</b>	<b>18.150</b>	<b>0.3971</b>	<b>8.044</b>	<b>0.0061</b>	<b>0.1116</b>	<b>0.3655</b>	<b>0.0460</b>	<b>0.0242</b>
<b>S<sub>M</sub></b>	0.0016	0.0084	0.0165	0.0013	0.0003	0.052	0.0081	0.039	0.0004	0.0023	0.0064	0.0019	0.0016
<b>S<sub>w</sub></b>	0.0006	0.0038	0.0079	0.0007	0.0001	0.061	0.0040	0.044	0.0003	0.0015	0.0035	0.0004	0.0005

Line No	Sn	Ti	V	W
1	0.0085	0.0004	0.0962	0.0278
2	0.0087	0.0004	0.0972	0.0283
3	0.0091	0.0004	0.0975	0.0293
4	0.0093	0.0005	0.0976	0.0294
5	0.0094	0.0005	0.0984	0.0298
6	0.0097	0.0005	0.0987	0.0299
7	0.0098	0.0007	0.0988	0.0303
8	0.0100	0.0008	0.0989	0.0303
9	0.0102	0.0008	0.0990	0.0304
10	0.0102	0.0009	0.0992	0.0308
11	0.0103	---	0.0993	0.0312
12	0.0103	---	0.0995	0.0312
13	0.0103		0.0996	0.0320
14	0.0103		0.0996	0.0329
15	0.0108		0.1001	0.0331
16	0.0110		0.1001	0.0336
17			0.1003	
18			0.1013	
19			0.1019	
<b>M<sub>M</sub></b>	<b>0.0099</b>	<b>0.0006</b>	<b>0.0991</b>	<b>0.0306</b>
<b>S<sub>M</sub></b>	0.0008	0.0002	0.0014	0.0017
<b>S<sub>w</sub></b>	0.0003	0.0001	0.0014	0.0006

Al(tot)	Pb
0.0006	< 0.0001
0.0008	< 0.0001
0.0008	< 0.0001
0.0015	< 0.0001
0.0019	< 0.0001
< 0.0020	0.0001
0.0024	0.0001
0.0028	0.0001
0.0029	0.0001
0.0032	0.0001
0.0035	0.0005
0.0036	0.0008
---	0.0011
---	---
< 0.0020	< 0.0020
< 0.0020	---
---	---

**M<sub>M</sub>:** Mean of the intralaboratory means

**S<sub>M</sub>:** Standard deviation of the intralaboratory means

**S<sub>w</sub>:** Intralaboratory standard deviation

The laboratory mean values have been examined statistically to eliminate outlying values.

Where a "—" appears in the table it indicates that an outlying value has been eliminated by either the Cochran or Grubbs Test.

Values reported as "less than" by the participating laboratories have not been taken into account in the statistical calculations.

Values given in *italic* are for information only.

**CERTIFIED VALUES - Mass content in %**

	C	Si	Mn	P	S	Cr	Mo	Ni	As
<b>M<sub>M</sub></b>	<b>0.0499</b>	<b>0.441</b>	<b>1.262</b>	<b>0.0313</b>	<b>0.0010</b>	<b>18.150</b>	<b>0.397</b>	<b>8.044</b>	<b>0.0061</b>
<b>C(95 %)</b>	<b>0.0009</b>	<b>0.004</b>	<b>0.009</b>	<b>0.0007</b>	<b>0.0002</b>	<b>0.027</b>	<b>0.004</b>	<b>0.020</b>	<b>0.0002</b>

  

	Co	Cu	N	Nb	Sn	Ti	V	W
<b>M<sub>M</sub></b>	<b>0.1116</b>	<b>0.366</b>	<b>0.0460</b>	<b>0.0242</b>	<b>0.0099</b>	<b>0.0006</b>	<b>0.0991</b>	<b>0.0306</b>
<b>C(95 %)</b>	<b>0.0012</b>	<b>0.003</b>	<b>0.0011</b>	<b>0.0009</b>	<b>0.0004</b>	<b>0.0002</b>	<b>0.0007</b>	<b>0.0009</b>

The half-width confidence interval C(95%) =  $\frac{t \times S_M}{\sqrt{n}}$  where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 sections 6.1 and 10.5.2

This certified reference material was prepared in accordance with the recommendations set out in ISO Guides 30 – 35 and issued by:



ArcelorMittal

**ArcelorMittal Maizières Research SA (formerly "IRSID")**

Voie Romaine, BP 30320, F-57283 Maizières-lès-Metz Cedex

On behalf of: The Iron and Steel Nomenclature Co-ordinating Committee (COCOR) of the ECISS, after approval by all the participating laboratories and all the producing organisations (France - ArcelorMittal Maizières Research SA & CTIF; Germany - Iron and Steel CRM Working Group; Stahlinstitut VDEh, BAM Bundesanstalt für Materialforschung und -prüfung & MPI für Eisenforschung; Nordic Countries - Nordic CRM Working Group).

## METHODS USED

Element	Line number	Methods
C	1.2.3.4.5.6.7.9.10.11.12.13.14 8	Combustion, infrared absorption Combustion, non-aqueous titration after absorption in organic solvent
Si	2.3.8.13.17 4.5.6.7.9.10.11.12.15.21 14.18 16 19 20	Gravimetry, dehydration with perchloric acid ICP-OES MAS, molybdenum blue, without extraction Gravimetry, dehydration with hydrochloric acid ICP-MS FAAS
Mn	1.4.7.8.9.10.11.12.13.15.16.17 3.5.6.14.18 19	ICP-OES MAS, periodate oxidation FAAS
P	1.6.8 2.10.15.17.20 3.14 4 5.7.9.11.12.13.16.18.19	MAS, molybdenum blue, without extraction MAS, phosphovanadomolybdate, extraction ICP-MS MAS, molybdenum blue, extraction ICP-OES
S	1.2.3.4.5.6.7.8.9.10.11.14 12 13	Combustion, infrared absorption MAS, methylene blue, evolution as H <sub>2</sub> S in hypophosphoric and formic acid medium Gravimetry as BaSO <sub>4</sub> without separation
Cr	3.4.6.10.11.12.15.16.17.18 5.7.8.9 13.14 19	ICP-OES Titration with Fe (II), oxidation with persulphate Titration with Fe (II), oxidation with peroxide Titration with Fe (II), oxidation with perchloric acid
Mo	1.2.4.5.6.8.9.10.11.12.14.15.17.18.19.21 3.13.20 7 16	ICP-OES MAS, thiocyanate in presence of Sn (II), extraction MAS, thiocyanate in presence of ascorbic acid, extraction ICP-MS
Ni	2 3.9.13 4.6.7.8.11.12.14.15.16.17.18.19 5 10	Titration with dichromate, separation with dimethylglyoxime Gravimetry, dimethylglyoxime ICP-OES Cyanometric titration MAS, dimethylglyoxime, extraction
As	1 2.6.11.12.15 3 4.7.10.13.14 5 8.9.17 16	MAS, DDC, separation as arsine ETAAS AAS, evolution as arsine ICP-OES ICP-OES, evolution as arsine ICP-MS Titration with iodine, precipitation of elemental As
Co	3.4.5.6.7.8.9.10.11.12.14.15.16.17.18 13 19	ICP-OES ETAAS ICP-MS
Cu	1.4 2.3.5.6.8.9.10.11.12.13.15.16.17.18.19.20.21 7 14	FAAS ICP-OES ICP-MS MAS, DDC, extraction
N	1.2.3.4.5.6.7.8.10.11.12 9.13.14	Thermal conductivity, decomposition in graphite crucible Acidimetric titration after distillation, visual end point
Nb	1.7 2.3.4.5.6.8.9.10.11.13.14.15.16.17	ICP-MS ICP-OES
Sn	1.3.5.7.8.9.10.11.12.15 2.4.16 6.13 14	ICP-OES ETAAS ICP-MS FAAS, extraction with TOPO/KI/MIBK
Ti	1.7.9 2.3.4.5.6.8.10	ICP-MS ICP-OES
V	1.2.3.4.6.7.8.9.10.11.12.14.15.16.17.18.19 5 13	ICP-OES ICP-MS MAS, hydrogen peroxide
W	1.2.4.5.6.7.8.11.12.13.14.15.16 3.9.10	ICP-OES ICP-MS
Al(tot)	1.3.5.7.8.9.11.12 2.6 4 10	ICP-OES ICP-MS ETAAS FAAS, without separation
Pb	1.2.4.5.7.9.11 3.8.10 6.16 12.17 13	ETAAS ICP-MS ICP-OES FAAS MAS, dithizone

## Abbreviations:

AAS	Atomic Absorption Spectrometry	ICP-MS	Inductively Coupled Plasma – Mass Spectrometry
ETAAS	Electrothermal Atomic Absorption Spectrometry	MAS	Molecular Absorption Spectrometry
DDC	Diethyldithiocarbamate	MIBK	Methylisobutylketone (4-methyl pentan-2-one)
FAAS	Flame Atomic Absorption Spectrometry	TOPO	Tri-octylphosphine oxide
ICP-OES	Inductively Coupled Plasma – Optical Emission Spectrometry		

## DESCRIPTION OF THE SAMPLE

The sample consists of chips passing a nominal 1000 µm aperture sieve from which the fines passing a nominal 250 µm sieve has been removed. It is supplied in bottles containing 100 g [ref ECRM 269-1(C)]. It is also supplied in the form of 35 mm dia. x 25 mm discs [ref ECRM 269-1 (D)].

## INTENDED USE & STABILITY

ECRM 269-1(C) is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where the calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the content should become discoloured (e.g. oxidised) due to atmospheric contamination it should be discarded.

The solid (disc) sample, ECRM 269-1(D), is intended for establishing and checking the calibration of optical emission and X-ray spectrometers for the analysis of samples of similar materials. The “as received” working surface of the sample should be finished before use to remove any protective coating. It will remain stable provided that it is not subjected to excessive heat (e.g. during preparation of the working surface).

## TRACEABILITY

**The traceability of ECRM 269-1 has been established in accordance with principles of ISO Guides 30 – 35 and the International vocabulary of basic and general terms in metrology.**

The assigned values for each material are achieved by inter-laboratory characterization, each laboratory using the method of their choice, details of which are given above. These methods are either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds. Most methods used were either international or national standard methods or methods which are technically equivalent.

## PARTICIPATING LABORATORIES

AB Sandvik Materials Technology, Sandviken (Sweden)  
AG der Dillinger Hüttenwerke, Dillingen/Saar (Germany)  
ALS Scandinavia AB, Luleå (Sweden)  
Aperam Imphy, Imphy (France)  
Aperam Isbergues, Isbergues (France)  
ArcelorMittal Maizières Research SA, Maizières-lès-Metz (France)  
Aubert & Duval, Les Ancizes (France)  
BAM Bundesanstalt für Materialforschung und -prüfung, Berlin (Germany)  
Böhler Edelstahl GmbH & Co. KG, Kapfenberg (Austria)  
CTIF, Sèvres (France)  
DCNS Centre Propulsion Nantes-Indret, La Montagne (France)  
Deutsche Edelstahlwerke GmbH, Witten (Germany)  
École des Mines de Saint-Etienne, Saint-Etienne (France)  
Element Materials Technology, Sheffield (UK)  
Eltra GmbH, Haan (Germany)  
Exova, Teesside (UK)  
Heraeus Materials Technology GmbH & Co. KG, Hanau (Germany)  
Höganäs Sweden AB, Höganäs (Sweden)  
Industeel France - Le Creusot, Le Creusot (France)  
Institute of Certified Reference Materials, Yekaterinburg (Russia)  
Leibniz-Institut für Festkörper- und Werkstoffforschung, Dresden (Germany)  
Ridsdale & Co. Ltd., Middlesbrough (UK)  
Saarstahl AG, Völklingen (Germany)  
Swerea KIMAB AB, Kista (Sweden)  
ThyssenKrupp Acciai Speciali Terni, Terni (Italy)  
Ugitech, Ugine (France)

## FURTHER INFORMATION

Pour disposer d'informations sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM-MRC) ainsi que sur l'utilisation des informations statistiques données sur ce certificat, se reporter soit au producteur de ce Matériau de Référence Certifié, soit aux Rapports Techniques CEN/TR 10317:2014 et CEN/TR 10350:2013. On peut se procurer ces deux documents auprès des organismes nationaux de normalisation. (Pour la France: AFNOR, 11 Avenue Francis de Pressensé, 93571 – St Denis la Plaine Cedex).

D'autres informations et avis au sujet de ce Matériau de Référence Certifié, ou de tout autre Matériau de Référence Certifié ou Matériau de Référence produit par ArcelorMittal Maizières Research SA, peuvent être demandés en contactant l'adresse figurant dans le bas de ce Certificat.

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMs) and the use of the statistical information given on this certificate, please refer either to the producer of this Certified Reference Material or to Technical Reports CEN/TR 10317:2014 and CEN/TR 10350:2013, both of which are available from the national standards body in your country. (In the UK this is the BSI, 389 Chiswick High Road, London W4 4AL).

Further information and advice on this or other Certified Reference Materials or Reference Materials produced by ArcelorMittal Maizières Research SA, may be obtained from the address below.

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Europäischen Zertifizierten Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendungen der in diesem Zertifikat enthaltenen statistischen Daten sind erhältlich beim Hersteller dieses zertifizierten Referenzmaterials, dessen Adresse auf diesem Zertifikat angegeben ist oder sie finden sich in den CEN-Reports CEN/TR 10317:2014 und CEN/TR 10350:2013, beide zu beziehen durch die nationalen Normenorganisationen (in Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstraße 4-10, 10787 Berlin).

Weitere Informationen und Hinweise zu diesem oder anderen durch ArcelorMittal Maizières Research SA hergestellten zertifizierten Referenzmaterialien oder Referenzmaterialien können unter der unten angegebenen Adresse erhalten werden.

För information angående tillverkning, certifiering och anskaffning av dessa europeiska certifierade referensmaterial (EURONORM CRM) och för användning av statistisk information, som angivits i detta certifikat, refereras antingen till producenten av detta certifierade referensmaterial eller till Teknisk Rapport CEN/TR 10317:2014 och CEN/TR 10350:2013 som kan erhållas från den nationella standardiseringsorganisationen. (Sverige: SIS, S:t Paulsgatan 6, SE-118 80 Stockholm, Finland: SFS, PL. 116, FIN-002 41, Helsingfors, Danmark: DS, Kollegievej 6, DK-Charlottenlund 2920, Norge: NSF, Drammensveien, 145 A, Postboks 353 Skøyen, NO-0213 Oslo, Island: STRI, Holtagardar, IS-104 Reykjavik).

Ytterligare information och rådfrågan om detta eller andra Certifierade Referensmaterial/Referensmaterial, producerade av ArcelorMittal Maizières Research SA, kan erhållas från angiven adress enligt nedan.

Laurence DAHERON  
Responsible for certification

ArcelorMittal Maizières Research SA  
Voie Romaine  
BP 30320  
57283 Maizières-lès-Metz Cedex  
France

E-mail: reference.materials@arcelormittal.com