

Basic Furnace slag - powder

Art. ID ECRM-S 883-1
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	6,55	%		
	Barium (Ba)	[7440-39-3]	0,0436	%		
	Calcium (Ca)	[7440-70-2]	21,32	%		
	Chromium (Cr)	[7440-47-3]	0,013	%		
	Iron (Fe)	[7439-89-6]	0,982	%		
	Potassium (K)	[7440-09-7]	0,393	%		
	Magnesium (Mg)	[7439-95-4]	8,86	%		
	Manganese (Mn)	[7439-96-5]	0,546	%		
	Molybdenum (Mo)	[7439-98-7]	<0,001	%		
	Sodium (Na)	[7440-23-5]	0,316	%		
	Nickel (Ni)	[7440-02-0]	0,00053	%		
	Phosphorus (P)	[7723-14-0]	0,0033	%		
	Sulfur (S)	[7704-34-9]	1,0885	%		
	Silicon (Si)	[7440-21-3]	16,67	%		
	Strontium (Sr)	[7440-24-6]	0,038	%		
	Titanium (Ti)	[7440-32-6]	1,3331	%		
	Vanadium (V)	[7440-62-2]	0,122	%		
	Zirconium (Zr)	[7440-67-7]	0,0276	%		