

Glass, SUS, Disc 40 mm Ø x 5 mm

| | |
|-----------------|-----------------------------------|
| Art. ID | XRF-BR-SOLO |
| Unit | disc |
| Deliverydetails | No Dangerous Good /not restricted |

Description

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|-------------------|------------|---------------------|------|--------|--------|
| | B2O3 | | 9,15 | % | | |
| | BaO | | 1,2 | % | | |
| | CaO | | 0,15 | % | | |
| | K2O | | 12 | % | | |
| | Na2O | | 17 | % | | |
| | Sb2O3 | | 0,5 | % | | |
| | SiO2 | | 55,5 | % | | |
| | SrO | | 1,5 | % | | |
| | ZnO | | 3,0 | % | | |