

Glass, SUS setting up standard, Disc 40 mm Ø x 5 mm

Art. ID	XRF-BR-BAXS-S2
Unit	disc
Deliverydetails	No Dangerous Good /not restricted

Description

The concentrations of all elements were calculated from the composition of the glass melt. Approximate composition in mass %.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
Approximate composition in mass %	SiO ₂		30	%		
Approximate composition in mass %	B ₂ O ₃		33,50	%		
Approximate composition in mass %	Na ₂ O		5,00	%		
Approximate composition in mass %	K ₂ O		2,00	%		
Approximate composition in mass %	CaO		15,00	%		
Approximate composition in mass %	MnO		7,00	%		
Approximate composition in mass %	As ₂ O ₃		2,00	%		
Approximate composition in mass %	MoO ₃		3,00	%		
Approximate composition in mass %	Sb ₂ O ₃		2,00	%		
Approximate composition in mass %	CoO		0,50	%		