

Calcined Bone, RM, Powder

Art. ID CERAM-CCB1-100G
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		2,6	%		
	Al ₂ O ₃		0,05	%		
	BaO		0,031	%		
	CaO		53,4	%		
	Fluorine (F)	[7782-41-4]	0,13	%		
	Fe ₂ O ₃		0,04	%		
	H ₂ O		~0,12	%		
	K ₂ O		0,011	%		
	MgO	[1309-48-4]	1,14	%		
	Na ₂ O		0,52	%		
	P ₂ O ₅		40,5	%		
	SO ₃		0,114	%		
	SiO ₂		1,28	%		
	SrO		0,049	%		
	TiO ₂		<0,01	%		