

Iron oxide recovered from pickling bath (Ruthner) - powder

Art. ID ECRM-D 686-1
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Iron (Fe)	[7439-89-6]	69,44	%		
	Silicon (Si)	[7440-21-3]	0,0083	%		
	Calcium (Ca)	[7440-70-2]	0,0097	%		
	Magnesium (Mg)	[7439-95-4]	0,0027	%		
	Aluminium (Al)	[7429-90-5]	0,0407	%		
	Titanium (Ti)	[7440-32-6]	0,0014	%		
	Manganese (Mn)	[7439-96-5]	0,231	%		
	Phosphorus (P)	[7723-14-0]	0,0078	%		
	Sodium (Na)	[7440-23-5]	0,0058	%		
	Potassium (K)	[7440-09-7]	0,0024	%		
	Chlorine (Cl)	[7782-50-5]	0,095	%		
	Chromium (Cr)	[7440-47-3]	0,0182	%		
	Cobalt (Co)	[7440-48-4]	0,0019	%		
	Copper (Cu)	[7440-50-8]	0,0038	%		
	Molybdenum (Mo)	[7439-98-7]	0,0007	%		
	Nickel (Ni)	[7440-02-0]	0,0127	%		
	Tin (Sn)	[7440-31-5]	0,0025	%		
	Zinc (Zn)	[7440-66-6]	0,0004	%		