

Titanium Alloy, Ti 3-2.5/UNS R56320, chips

Art. ID IARM-261B-C
Unit 65 g (chips)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|-------------------|-------------|---------------------|------|--------|--------|
| | Aluminium (Al) | [7429-90-5] | 2,98 | % | | |
| | Boron (B) | [7440-42-8] | 0,0004 | % | | |
| | Carbon (C) | [7440-44-0] | 0,011 | % | | |
| | Cobalt (Co) | [7440-48-4] | <0,004 | % | | |
| | Chromium (Cr) | [7440-47-3] | 0,016 | % | | |
| | Copper (Cu) | [7440-50-8] | 0,003 | % | | |
| | Iron (Fe) | [7439-89-6] | 0,19 | % | | |
| | Hydrogen (H) | [1333-74-0] | ~0,001 | % | | |
| | Manganese (Mn) | [7439-96-5] | ~0,003 | % | | |
| | Molybdenum (Mo) | [7439-98-7] | 0,004 | % | | |
| | Nitrogen (N) | [7727-37-9] | 0,004 | % | | |
| | Niobium (Nb) | [7440-03-1] | ~0,002 | % | | |
| | Nickel (Ni) | [7440-02-0] | 0,023 | % | | |
| | Oxygen (O) | [7782-44-7] | 0,083 | % | | |
| | Phosphorus (P) | [7723-14-0] | ~0,004 | % | | |
| | Ruthenium (Ru) | [7440-18-8] | ~0,001 | % | | |
| | Sulfur (S) | [7704-34-9] | ~0,0004 | % | | |
| | Silicon (Si) | [7440-21-3] | 0,008 | % | | |
| | Tin (Sn) | [7440-31-5] | 0,004 | % | | |
| | Titanium (Ti) | [7440-32-6] | ~94,4 | % | | |
| | Vanadium (V) | [7440-62-2] | 2,23 | % | | |
| | Tungsten (W) | [7440-33-7] | ~0,003 | % | | |
| | Yttrium (Y) | [7440-65-5] | ~0,0004 | % | | |
| | Zirconium (Zr) | [7440-67-7] | ~0,002 | % | | |