

**Nickel Alloy, Haynes 214 Alloy/UNS N07214, disc 38 x 19 mm (formerly IARM-61)**

Art. ID IARM-NIH214-18-G  
Unit disc  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	4,28	%		
	Boron (B)	[7440-42-8]	0,0033	%		
	Carbon (C)	[7440-44-0]	0,036	%		
	Cobalt (Co)	[7440-48-4]	~0,007	%		
	Chromium (Cr)	[7440-47-3]	16,24	%		
	Copper (Cu)	[7440-50-8]	0,0011	%		
	Iron (Fe)	[7439-89-6]	3,48	%		
	Magnesium (Mg)	[7439-95-4]	0,0053	%		
	Manganese (Mn)	[7439-96-5]	0,185	%		
	Molybdenum (Mo)	[7439-98-7]	~0,004	%		
	Nitrogen (N)	[7727-37-9]	0,0026	%		
	Niobium (Nb)	[7440-03-1]	~0,003	%		
	Nickel (Ni)	[7440-02-0]	75,6	%		
	Phosphorus (P)	[7723-14-0]	~0,0017	%		
	Sulfur (S)	[7704-34-9]	~0,0004	%		
	Silicon (Si)	[7440-21-3]	0,02	%		
	Titanium (Ti)	[7440-32-6]	~0,003	%		
	Vanadium (V)	[7440-62-2]	~0,003	%		
	Tungsten (W)	[7440-33-7]	~0,02	%		
	Zirconium (Zr)	[7440-67-7]	0,026	%		
	Aluminium (Al)	[7429-90-5]	4,28	%		
	Boron (B)	[7440-42-8]	0,0033	%		
	Carbon (C)	[7440-44-0]	0,036	%		
	Cobalt (Co)	[7440-48-4]	~0,007	%		
	Chromium (Cr)	[7440-47-3]	16,24	%		
	Copper (Cu)	[7440-50-8]	0,0011	%		
	Iron (Fe)	[7439-89-6]	3,48	%		
	Magnesium (Mg)	[7439-95-4]	0,0053	%		
	Manganese (Mn)	[7439-96-5]	0,185	%		
	Molybdenum (Mo)	[7439-98-7]	~0,004	%		
	Nitrogen (N)	[7727-37-9]	0,0026	%		

Niobium (Nb)	[7440-03-1]	~0,003	%
Nickel (Ni)	[7440-02-0]	75,6	%
Phosphorus (P)	[7723-14-0]	~0,0017	%
Sulfur (S)	[7704-34-9]	~0,0004	%
Silicon (Si)	[7440-21-3]	0,02	%
Titanium (Ti)	[7440-32-6]	~0,003	%
Vanadium (V)	[7440-62-2]	~0,003	%
Tungsten (W)	[7440-33-7]	~0,02	%
Zirconium (Zr)	[7440-67-7]	0,026	%