

Iron base, Steel - Resulfurized Stainless, CRM, 420F S, Chips 100 g

Art. ID IARM-352A-C
Unit 100 g (chips)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	~0,0025	%		
	Arsenic (As)	[7440-38-2]	~0,005	%		
	Boron (B)	[7440-42-8]	~0,0007	%		
	Carbon (C)	[7440-44-0]	0,341	%		
	Cobalt (Co)	[7440-48-4]	~0,016	%		
	Chromium (Cr)	[7440-47-3]	13,11	%		
	Copper (Cu)	[7440-50-8]	0,148	%		
	Manganese (Mn)	[7439-96-5]	1,13	%		
	Molybdenum (Mo)	[7439-98-7]	0,38	%		
	Nitrogen (N)	[7727-37-9]	0,029	%		
	Niobium (Nb)	[7440-03-1]	~0,012	%		
	Nickel (Ni)	[7440-02-0]	0,269	%		
	Oxygen (O)	[7782-44-7]	~0,005	%		
	Phosphorus (P)	[7723-14-0]	0,0182	%		
	Sulfur (S)	[7704-34-9]	0,21	%		
	Selenium (Se)	[7782-49-2]	~0,006	%		
	Silicon (Si)	[7440-21-3]	0,357	%		
	Tin (Sn)	[7440-31-5]	0,0046	%		
	Tantalum (Ta)	[7440-25-7]	~0,0007	%		
	Titanium (Ti)	[7440-32-6]	0,0015	%		
	Vanadium (V)	[7440-62-2]	0,028	%		
	Tungsten (W)	[7440-33-7]	~0,005	%		