

Iron base, Steel - Stainless, CRM, 347, Chips 100 g

Art. ID IARM-8I-C
Unit 100 g (chips)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	~0,003	%		
	Boron (B)	[7440-42-8]	~0,0005	%		
	Carbon (C)	[7440-44-0]	0,0424	%		
	Cobalt (Co)	[7440-48-4]	0,301	%		
	Chromium (Cr)	[7440-47-3]	17,08	%		
	Copper (Cu)	[7440-50-8]	0,441	%		
	Manganese (Mn)	[7439-96-5]	1,395	%		
	Molybdenum (Mo)	[7439-98-7]	0,416	%		
	Nitrogen (N)	[7727-37-9]	0,052	%		
	Niobium (Nb)	[7440-03-1]	0,6	%		
	Nickel (Ni)	[7440-02-0]	9,01	%		
	Oxygen (O)	[7782-44-7]	~0,004	%		
	Phosphorus (P)	[7723-14-0]	0,0352	%		
	Sulfur (S)	[7704-34-9]	0,0118	%		
	Silicon (Si)	[7440-21-3]	0,38	%		
	Tin (Sn)	[7440-31-5]	~0,012	%		
	Titanium (Ti)	[7440-32-6]	~0,008	%		
	Vanadium (V)	[7440-62-2]	0,057	%		
	Tungsten (W)	[7440-33-7]	0,06	%		
	Aluminium (Al)	[7429-90-5]	~0,0030	%		
	Boron (B)	[7440-42-8]	~0,0005	%		
	Carbon (C)	[7440-44-0]	0,0424	%		
	Cobalt (Co)	[7440-48-4]	0,301	%		
	Chromium (Cr)	[7440-47-3]	17,08	%		
	Copper (Cu)	[7440-50-8]	0,441	%		
	Manganese (Mn)	[7439-96-5]	1,395	%		
	Molybdenum (Mo)	[7439-98-7]	0,416	%		
	Nitrogen (N)	[7727-37-9]	0,052	%		
	Niobium (Nb)	[7440-03-1]	0,6	%		
	Nickel (Ni)	[7440-02-0]	9,01	%		
	Oxygen (O)	[7782-44-7]	~0,004	%		

Phosphorus (P)	[7723-14-0]	0,0352	%
Sulfur (S)	[7704-34-9]	0,0118	%
Silicon (Si)	[7440-21-3]	0,38	%
Tin (Sn)	[7440-31-5]	~0,012	%
Titanium (Ti)	[7440-32-6]	~0,008	%
Vanadium (V)	[7440-62-2]	0,057	%
Tungsten (W)	[7440-33-7]	0,06	%