

Slag, CRM, Blast Furnace Slag

Art. ID NCS HC28804
Unit 60 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		16,26	%		
	CaO		37,13	%		
	Iron (Fe)	[7439-89-6]	2,01	%		
	MgO	[1309-48-4]	7,52	%		
	MnO ₂		1,23	%		
	P ₂ O ₅		0,043	%		
	Sulfur (S)	[7704-34-9]	0,79	%		
	SiO ₂		31,18	%		
	TiO ₂		0,58	%		