

## **Slag, CRM, Blast Furnace Slag**

Art. ID                      NCS HC28804  
Unit                         60 g  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		16,26	%		
	CaO		37,13	%		
	Iron (Fe)	[7439-89-6]	2,01	%		
	MgO	[1309-48-4]	7,52	%		
	MnO <sub>2</sub>		1,23	%		
	P <sub>2</sub> O <sub>5</sub>		0,043	%		
	Sulfur (S)	[7704-34-9]	0,79	%		
	SiO <sub>2</sub>		31,18	%		
	TiO <sub>2</sub>		0,58	%		