

Slag, CRM, Blast Furnace Slag

Art. ID NCS HC28805
Unit 60 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		12,8	%		
	CaO		39,2	%		
	Iron (Fe)	[7439-89-6]	0,76	%		
	MgO	[1309-48-4]	9,27	%		
	MnO ₂		0,09	%		
	P ₂ O ₅		0,012	%		
	Sulfur (S)	[7704-34-9]	0,9	%		
	SiO ₂		34,91	%		
	TiO ₂		0,42	%		