

## **Burnt refractory (Al<sub>2</sub>O<sub>3</sub> - 60%) - Constituents (powder)**

Art. ID                      NIST-77a  
Unit                         75 g  
Deliverydetails            No Dangerous Good /not restricted

### Description

This Standard Reference Material (SRM®) is in the form of fine powder (<0.15 mm). Certified values /// Sample value(s) - please ask for current certificate.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	SiO <sub>2</sub>		35	%		
	Al <sub>2</sub> O <sub>3</sub>		60,2	%		
	Fe <sub>2</sub> O <sub>3</sub>		1	%		
	TiO <sub>2</sub>		2,66	%		
	MgO	[1309-48-4]	0,38	%		
	CaO		0,05	%		
	K <sub>2</sub> O		0,090	%		
	Na <sub>2</sub> O		0,037	%		
	P <sub>2</sub> O <sub>5</sub>		0,092	%		
	Li <sub>2</sub> O		0,025	%		
	SrO		0,009	%		