

Resulfurized Steel Set/4 discs

Art. ID	BS-RESUL-4
Unit	set of 4 discs
Deliverydetails	No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Aluminium (Al)	[7429-90-5]	~0,002	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Arsenic (As)	[7440-38-2]	~0,008	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Carbon (C)	[7440-44-0]	0,15	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Cobalt (Co)	[7440-48-4]	~0,007	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Chromium (Cr)	[7440-47-3]	0,066	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Copper (Cu)	[7440-50-8]	0,24	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)	Manganese (Mn)	[7439-96-5]	1,19	%		
BS-65C-7MM: Iron, 1117, Resulfurized Steel, RM , 7 mm disc (see also s	Molybdenum (Mo)	[7439-98-7]	0,012	%		

et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Nitrogen (N)	[7727-37-9]	0,0084		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Nickel (Ni)	[7440-02-0]	0,063		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Phosphorus (P)	[7723-14-0]	0,007		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Sulfur (S)	[7704-34-9]	0,115		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Silicon (Si)	[7440-21-3]	0,24		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Tin (Sn)	[7440-31-5]	0,02		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-65C-7MM: Iron, 1117,	Vanadium (V)	[7440-62-2]	0,002		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Aluminium (Al)	[7429-90-5]	0,028		%
+P, Resulfurized Steel, RM, 7 mm disc (see als					
o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Carbon (C)	[7440-44-0]	0,436		%
+P, Resulfurized Steel, RM, 7 mm disc (see als					
o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Cobalt (Co)	[7440-48-4]	0,012		%

+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Chromium (Cr)	[7440-47-3]	0,16		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Copper (Cu)	[7440-50-8]	0,06		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Manganese (Mn)	[7439-96-5]	0,97		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Molybdenum (Mo)	[7439-98-7]	0,09		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Nitrogen (N)	[7727-37-9]	0,0025		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Nickel (Ni)	[7440-02-0]	0,18		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Oxygen (O)	[7782-44-7]	~0,002		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Phosphorus (P)	[7723-14-0]	0,068		%
+P, Resulturized Steel, RM, 7 mm disc (see als o set BS-RESUL-4)					
BS-52D-7MM: Iron, 1140	Sulfur (S)	[7704-34-9]	0,088		%
+P, Resulturized Steel, RM, 7 mm disc (see als					

o set BS-RESUL-4)

BS-52D-7MM: Iron, 1140 Silicon (Si) [7440-21-3] 0,18 %

+P, Resulfurized Steel,
RM, 7 mm disc (see als

o set BS-RESUL-4)

BS-52D-7MM: Iron, 1140 Tin (Sn) [7440-31-5] 0,004 %

+P, Resulfurized Steel,
RM, 7 mm disc (see als

o set BS-RESUL-4)

BS-52D-7MM: Iron, 1140 Titanium (Ti) [7440-32-6] ~0,004 %

+P, Resulfurized Steel,
RM, 7 mm disc (see als

o set BS-RESUL-4)

BS-52D-7MM: Iron, 1140 Vanadium (V) [7440-62-2] 0,002 %

+P, Resulfurized Steel,
RM, 7 mm disc (see als

o set BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Aluminium (Al) [7429-90-5] 0,002 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Carbon (C) [7440-44-0] 0,418 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Cobalt (Co) [7440-48-4] 0,005 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Chromium (Cr) [7440-47-3] 0,094 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Copper (Cu) [7440-50-8] 0,031 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Manganese (Mn) [7439-96-5] 1,57 %

Resulfurized Steel, RM

, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Molybdenum (Mo) [7439-98-7] 0,019 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Nitrogen (N) [7727-37-9] ~0,006 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Nickel (Ni) [7440-02-0] 0,033 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Phosphorus (P) [7723-14-0] 0,018 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Sulfur (S) [7704-34-9] 0,11 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Silicon (Si) [7440-21-3] 0,02 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Tin (Sn) [7440-31-5] 0,001 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66B-7MM: Iron, 1141, Vanadium (V) [7440-62-2] 0,002 %

Resulfurized Steel, RM
, 7 mm disc(see also s
et BS-RESUL-4)

BS-66K-7MM: Iron, 1215, Aluminium (Al) [7429-90-5] 0,002 %

Resulfurized Steel, RM
, 7 mm disc(see also s

et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Carbon (C)	[7440-44-0]	0,051		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Cobalt (Co)	[7440-48-4]	0,005		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Chromium (Cr)	[7440-47-3]	0,006		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Copper (Cu)	[7440-50-8]	0,013		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Manganese (Mn)	[7439-96-5]	0,86		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Molybdenum (Mo)	[7439-98-7]	0,003		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Nitrogen (N)	[7727-37-9]	~0,0074		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Nickel (Ni)	[7440-02-0]	0,012		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Phosphorus (P)	[7723-14-0]	0,062		%
Resulfurized Steel, RM , 7 mm disc (see also s					
et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Sulfur (S)	[7704-34-9]	0,322		%

Resulturized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Silicon (Si)	[7440-21-3]	~0,004		%
Resulturized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Tin (Sn)	[7440-31-5]	<0,001		%
Resulturized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)					
BS-66K-7MM: Iron, 1215,	Vanadium (V)	[7440-62-2]	0,001		%
Resulturized Steel, RM , 7 mm disc (see also s et BS-RESUL-4)					