

## **Feldspar**

Art. ID                      FLX-CRM129  
Unit                            each  
Deliverydetails            No Dangerous Good /not restricted

### **Description**

Certified value traceable to SI unit kg/kg based on dried sample material for 1 hour at 105°C

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
certified value	Al <sub>2</sub> O <sub>3</sub>		16,44	%		
certified value	BaO		0,13	%		
certified value	CaO		0,374	%		
certified value	Fe <sub>2</sub> O <sub>3</sub>		0,104	%		
certified value	K <sub>2</sub> O		10,78	%		
certified value	Na <sub>2</sub> O		2,11	%		
certified value	P <sub>2</sub> O <sub>5</sub>		0,068	%		
certified value	SiO <sub>2</sub>		69,84	%		
informational value	SrO		0,014	%		
informational value	TiO <sub>2</sub>		0,036	%		
informational value	Loss on Ignition (L.O.I ) (1h at 950°C)		0,428	%		