

**ARCONIC - Aluminium base 6061, Class: RM, Alloy: 6061, cast, Disc 64 mm x 25 mm**

Art. ID ALCOA-SS-6061  
Unit disc  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Silver (Ag)	[7440-22-4]	<0,0010	%		
	Arsenic (As)	[7440-38-2]	<0,0010	%		
	Boron (B)	[7440-42-8]	<0,0010	%		
	Beryllium (Be)	[7440-41-7]	<0,0005	%		
	Bismuth (Bi)	[7440-69-9]	<0,0010	%		
	Calcium (Ca)	[7440-70-2]	<0,0005	%		
	Cadmium (Cd)	[7440-43-9]	<0,0010	%		
	Cobalt (Co)	[7440-48-4]	<0,0010	%		
	Chromium (Cr)	[7440-47-3]	0,23	%		
	Copper (Cu)	[7440-50-8]	0,3	%		
	Iron (Fe)	[7439-89-6]	0,35	%		
	Gallium (Ga)	[7440-55-3]	0,02i	%		
	Mercury (Hg)	[7439-97-6]	<0,0005	%		
	Lithium (Li)	[7439-93-2]	<0,0005	%		
	Magnesium (Mg)	[7439-95-4]	1,0i	%		
	Manganese (Mn)	[7439-96-5]	0,05i	%		
	Sodium (Na)	[7440-23-5]	<0,0005	%		
	Nickel (Ni)	[7440-02-0]	0,05i	%		
	Phosphorus (P)	[7723-14-0]	<0,0010	%		
	Lead (Pb)	[7439-92-1]	<0,0030	%		
	Antimony (Sb)	[7440-36-0]	<0,0010	%		
	Scandium (Sc)	[7440-20-2]	<0,0010	%		
	Silicon (Si)	[7440-21-3]	0,65	%		
	Tin (Sn)	[7440-31-5]	<0,0010	%		
	Strontium (Sr)	[7440-24-6]	<0,0010	%		
	Titanium (Ti)	[7440-32-6]	0,04i	%		
	Vanadium (V)	[7440-62-2]	0,01i	%		
	Zinc (Zn)	[7440-66-6]	0,08i	%		
	Zirconium (Zr)	[7440-67-7]	<0,0030	%		