

Portland Composite Cement with limestone, Powder

Art. ID TL-204CA
Unit 40 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | 11,6 | % | | |
| | Insoluble Residue | | 1,38 | % | | |
| | Al ₂ O ₃ | | 3,5 | % | | |
| | CaO | | 59,84 | % | | |
| | Free CaO | | 0,47 | % | | |
| | Fe ₂ O ₃ | | 1,81 | % | | |
| | K ₂ O | | 0,52 | % | | |
| | MgO | [1309-48-4] | 3,05 | % | | |
| | Na ₂ O | | 0,15 | % | | |
| | SO ₃ | | 2,75 | % | | |
| | SiO ₂ | | 16,31 | % | | |