

*****sold out*** Bauxite, CRM**

Art. ID CETEM-BXBA-3
Unit 110 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Alumina		53,99 ± 0,33	%		
	Reactive silica		1,075 ± 0,045	%		
	Al ₂ O ₃		56,46 ± 0,36	%		
	Fe ₂ O ₃		8,406 ± 0,081	%		
	SiO ₂		2,911 ± 0,041	%		
	MnO ₂		0,0222 ± 0,0019	%		
	P ₂ O ₅		0,1563 ± 0,0028	%		
	SO ₃		0,2282 ± 0,0088	%		
	TiO ₂		0,964 ± 0,026	%		
	V ₂ O ₅		0,0166 ± 0,0030	%		
	ZrO ₂		0,0176 ± 0,0031	%		
405°C	Loss on Ignition (L.O.I)		27,20 ± 0,35	%		
1000 °C	Loss on Ignition (L.O.I)		30,98 ± 0,13	%		