

**Albite Nano-Pellet, pressed pellet diameter 20 mm (Standard for solid-state microanalysis)**

Art. ID MY-AL-I-NP-LA-ICP-MS-LIBS-20MM  
Unit each (pressed pellet)  
Deliverydetails No Dangerous Good /not restricted

Description

Pellet for LA-ICP-MS and LIBS application /// The principle behind LA-ICP-MS (Laser Ablation - Inductively Coupled Plasma - Mass Spectrometry) involves a laser beam removing (ablating) material from a sample and analysing its chemical composition in a mass spectrometer /// LIBS (Laser-Induced Breakdown Spectroscopy) uses a laser beam to interact with the sample. Due to the extreme heat of the laser (10,000 K and more) a plasma is formed. A plasma is a cloud of ions (charged atoms) and electrons (negatively charged particles). When this plasma collapses it emits light. Light is a mixture of different wavelengths. This light is then transferred through a fiberoptic cable to a spectrometer, which can precisely split the light into its respective wavelengths. The working principle of the LIBS-spectrometer is similar to a prism as it disperses the incoming light. Each element has several characteristic wavelengths. A detector is able to attribute an intensity to each of them.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Na2O		10,59 ± 0,1	g/100g		
	MgO	[1309-48-4]	0,035 ± 0,01	g/100g		
	Al2O3		18,59 ± 0,1	g/100g		
	SiO2		69,34 ± 0,16	g/100g		
	P2O5		0,038 ± 0,01	g/100g		
	K2O		0,14 ± 0,01	g/100g		
	CaO		0,384 ± 0,02	g/100g		
	TiO2		0,012 ± 0,004	g/100g		
	MnO		0,004 ± 0,002	g/100g		
	Fe2O3(T)		0,075 ± 0,01	g/100g		
	Lithium (Li)	[7439-93-2]	1 ± 0,14	µg/g		
	Beryllium (Be)	[7440-41-7]	2,7 ± 0,3	µg/g		
	Fluorine (F)	[7782-41-4]	45 ± 7	µg/g		
	Scandium (Sc)	[7440-20-2]	1,75 ± 0,2	µg/g		
	Vanadium (V)	[7440-62-2]	2 ± 1	µg/g		
	Chromium (Cr)	[7440-47-3]	2 ± 1	µg/g		
	Cobalt (Co)	[7440-48-4]	0,2 ± 0,1	µg/g		
	Nickel (Ni)	[7440-02-0]	2 ± 1	µg/g		
	Copper (Cu)	[7440-50-8]	3 ± 0,5	µg/g		
	Zinc (Zn)	[7440-66-6]	6 ± 1,5	µg/g		
	Gallium (Ga)	[7440-55-3]	20 ± 0,5	µg/g		
	Arsenic (As)	[7440-38-2]	0,8 ± 0,4	µg/g		
	Rubidium (Rb)	[7440-17-7]	5,8 ± 0,5	µg/g		

Strontium (Sr)	[7440-24-6]	80 ± 5	µg/g
Yttrium (Y)	[7440-65-5]	6,8 ± 0,4	µg/g
Zirconium (Zr)	[7440-67-7]	40 ± 4	µg/g
Niobium (Nb)	[7440-03-1]	1,6 ± 0,3	µg/g
Molybdenum (Mo)	[7439-98-7]	0,1 ± 0,03	µg/g
Tin (Sn)	[7440-31-5]	0,4 ± 0,2	µg/g
Antimony (Sb)	[7440-36-0]	0,2 ± 0,1	µg/g
Caesium (Cs)	[7440-46-2]	0,34 ± 0,1	µg/g
Barium (Ba)	[7440-39-3]	85 ± 6	µg/g
Lanthanum (La)	[7439-91-0]	9,5 ± 0,6	µg/g
Cerium (Ce)	[7440-45-1]	21 ± 1	µg/g
Praseodymium (Pr)	[7440-10-0]	2,8 ± 0,3	µg/g
Neodymium (Nd)	[7440-00-8]	10,4 ± 0,6	µg/g
Samarium (Sm)	[7440-19-9]	2,8 ± 0,3	µg/g
Europium (Eu)	[7440-53-1]	0,19 ± 0,02	µg/g
Gadolinium (Gd)	[7440-54-2]	1,9 ± 0,2	µg/g
Terbium (Tb)	[7440-27-9]	0,3 ± 0,06	µg/g
Dysprosium (Dy)	[7429-91-6]	1,5 ± 0,2	µg/g
Holmium (Ho)	[7440-60-0]	0,28 ± 0,05	µg/g
Erbium (Er)	[7440-52-0]	0,6 ± 0,1	µg/g
Thulium (Tm)	[7440-30-4]	0,1 ± 0,015	µg/g
Ytterbium (Yb)	[7440-64-4]	0,7 ± 0,1	µg/g
Lutetium (Lu)	[7439-94-3]	0,13 ± 0,02	µg/g
Hafnium (Hf)	[7440-58-6]	2,6 ± 0,2	µg/g
Tantalum (Ta)	[7440-25-7]	1,9 ± 0,3	µg/g
Tungsten (W)	[7440-33-7]	0,2 ± 0,1	µg/g
Lead (Pb)	[7439-92-1]	4,5 ± 0,7	µg/g
Thorium (Th)	[7440-29-1]	9,5 ± 1	µg/g
Uranium (U)	[7440-61-1]	5,8 ± 0,6	µg/g