

**Dunite Nano-Pellet, pressed pellet diameter 13 mm (Standard for solid-state microanalysis)**

Art. ID MY-DTS-2b-NP-uXRF-13MM  
Unit each (pressed pellet)  
Deliverydetails No Dangerous Good /not restricted

**Description**

Pellet for Micro-X-ray fluorescence spectroscopy application /// In micro X-ray fluorescence analysis, a sample is excited by X-rays. Depending on the energy of the X-rays and the material properties, the penetration depth of the X-rays and thus the excited volume may differ

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	MgO	[1309-48-4]	49,4 ± 1,8	g/100g		
	Al <sub>2</sub> O <sub>3</sub>		0,45 ± 0,06	g/100g		
	SiO <sub>2</sub>		39,4 ± 0,8	g/100g		
	CaO		0,12 ± 0,01	g/100g		
	Fe <sub>2</sub> O <sub>3</sub> (T)		7,76 ± 0,21	g/100g		
	Magnesium (Mg)	[7439-95-4]	298000 ± 11000	µg/g		
	Aluminium (Al)	[7429-90-5]	2400 ± 300	µg/g		
	Silicon (Si)	[7440-21-3]	184000 ± 4000	µg/g		
	Calcium (Ca)	[7440-70-2]	900 ± 100	µg/g		
	Vanadium (V)	[7440-62-2]	22 ± 8	µg/g		
	Chromium (Cr)	[7440-47-3]	15500 ± 1100	µg/g		
	Manganese (Mn)	[7439-96-5]	830 ± 40	µg/g		
	Fe(total)		54300 ± 1500	µg/g		
	Cobalt (Co)	[7440-48-4]	120 ± 10	µg/g		
	Nickel (Ni)	[7440-02-0]	3780 ± 220	µg/g		
	Zinc (Zn)	[7440-66-6]	45 ± 5	µg/g		