

**Granite Nano-Pellet, pressed pellet diameter 20 mm (Standard for solid-state microanalysis)**

Art. ID MY-GH-NP-LA-ICP-MS-LIBS-20MM  
Unit each (pressed pellet)  
Deliverydetails No Dangerous Good /not restricted

Description

Pellet for LA-ICP-MS and LIBS application /// The principle behind LA-ICP-MS (Laser Ablation - Inductively Coupled Plasma - Mass Spectrometry) involves a laser beam removing (ablating) material from a sample and analysing its chemical composition in a mass spectrometer /// LIBS (Laser-Induced Breakdown Spectroscopy) uses a laser beam to interact with the sample. Due to the extreme heat of the laser (10,000 K and more) a plasma is formed. A plasma is a cloud of ions (charged atoms) and electrons (negatively charged particles). When this plasma collapses it emits light. Light is a mixture of different wavelengths. This light is then transferred through a fiberoptic cable to a spectrometer, which can precisely split the light into its respective wavelengths. The working principle of the LIBS-spectrometer is similar to a prism as it disperses the incoming light. Each element has several characteristic wavelengths. A detector is able to attribute an intensity to each of them.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Na <sub>2</sub> O		3,85 ± 0,07	g/100g		
	MgO	[1309-48-4]	0,03 ± 0,015	g/100g		
	Al <sub>2</sub> O <sub>3</sub>		12,5 ± 0,1	g/100g		
	SiO <sub>2</sub>		75,8 ± 0,18	g/100g		
	P <sub>2</sub> O <sub>5</sub>		0,01 ± 0,005	g/100g		
	K <sub>2</sub> O		4,76 ± 0,05	g/100g		
	CaO		0,69 ± 0,04	g/100g		
	TiO <sub>2</sub>		0,08 ± 0,01	g/100g		
	MnO		0,05 ± 0,002	g/100g		
	Fe <sub>2</sub> O <sub>3</sub> (T)		1,34 ± 0,07	g/100g		
	Lithium (Li)	[7439-93-2]	45 ± 5	µg/g		
	Beryllium (Be)	[7440-41-7]	5,5 ± 0,8	µg/g		
	Fluorine (F)	[7782-41-4]	3500 ± 200	µg/g		
	Chlorine (Cl)	[7782-50-5]	100 ±	µg/g		
	Scandium (Sc)	[7440-20-2]	0,8 ± 0,5	µg/g		
	Vanadium (V)	[7440-62-2]	5 ± 3	µg/g		
	Chromium (Cr)	[7440-47-3]	3 ± 1	µg/g		
	Cobalt (Co)	[7440-48-4]	0,3 ± 0,1	µg/g		
	Nickel (Ni)	[7440-02-0]	3 ± 1,5	µg/g		
	Copper (Cu)	[7440-50-8]	3 ± 1,5	µg/g		
	Zinc (Zn)	[7440-66-6]	55 ± 5	µg/g		
	Gallium (Ga)	[7440-55-3]	23 ± 1,5	µg/g		
	Arsenic (As)	[7440-38-2]	0,4 ± 0,1	µg/g		

Rubidium (Rb)	[7440-17-7]	390 ± 10	µg/g
Strontium (Sr)	[7440-24-6]	8,7 ±	µg/g
Yttrium (Y)	[7440-65-5]	75 ± 3	µg/g
Zirconium (Zr)	[7440-67-7]	150 ± 20	µg/g
Niobium (Nb)	[7440-03-1]	85 ± 5	µg/g
Molybdenum (Mo)	[7439-98-7]	2 ± 0,4	µg/g
Tin (Sn)	[7440-31-5]	10 ± 2	µg/g
Caesium (Cs)	[7440-46-2]	2,5 ± 0,2	µg/g
Barium (Ba)	[7440-39-3]	20 ± 3	µg/g
Lanthanum (La)	[7439-91-0]	25 ± 1	µg/g
Cerium (Ce)	[7440-45-1]	60 ± 3	µg/g
Praseodymium (Pr)	[7440-10-0]	7,8 ± 0,5	µg/g
Neodymium (Nd)	[7440-00-8]	29 ± 2	µg/g
Samarium (Sm)	[7440-19-9]	9 ± 0,4	µg/g
Europium (Eu)	[7440-53-1]	0,12 ± 0,02	µg/g
Gadolinium (Gd)	[7440-54-2]	9,5 ± 0,8	µg/g
Terbium (Tb)	[7440-27-9]	1,9 ± 0,2	µg/g
Dysprosium (Dy)	[7429-91-6]	12 ± 0,6	µg/g
Holmium (Ho)	[7440-60-0]	2,9 ± 0,3	µg/g
Erbium (Er)	[7440-52-0]	8 ± 0,4	µg/g
Thulium (Tm)	[7440-30-4]	1,3 ± 0,1	µg/g
Ytterbium (Yb)	[7440-64-4]	8 ± 0,6	µg/g
Lutetium (Lu)	[7439-94-3]	1,1 ± 0,15	µg/g
Hafnium (Hf)	[7440-58-6]	6,6 ± 0,5	µg/g
Tantalum (Ta)	[7440-25-7]	4,8 ± 0,4	µg/g
Tungsten (W)	[7440-33-7]	1,6 ± 0,4	µg/g
Thallium (Tl)	[7440-28-0]	1,8 ± 0,4	µg/g
Lead (Pb)	[7439-92-1]	45 ± 4,4	µg/g
Thorium (Th)	[7440-29-1]	87 ± 8	µg/g
Uranium (U)	[7440-61-1]	18 ± 1	µg/g