

Serpentinite Nano-Pellet, pressed pellet diameter 32 mm (Standard for solid-state microanalysis)

Art. ID MY-UB-N-NP-LA-ICP-MS-LIBS-32MM
Unit each (pressed pellet)
Deliverydetails No Dangerous Good /not restricted

Description

Pellet for LA-ICP-MS and LIBS application /// The principle behind LA-ICP-MS (Laser Ablation - Inductively Coupled Plasma - Mass Spectrometry) involves a laser beam removing (ablating) material from a sample and analysing its chemical composition in a mass spectrometer /// LIBS (Laser-Induced Breakdown Spectroscopy) uses a laser beam to interact with the sample. Due to the extreme heat of the laser (10,000 K and more) a plasma is formed. A plasma is a cloud of ions (charged atoms) and electrons (negatively charged particles). When this plasma collapses it emits light. Light is a mixture of different wavelengths. This light is then transferred through a fiberoptic cable to a spectrometer, which can precisely split the light into its respective wavelengths. The working principle of the LIBS-spectrometer is similar to a prism as it disperses the incoming light. Each element has several characteristic wavelengths. A detector is able to attribute an intensity to each of them.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Na ₂ O		0,1 ± 0,04	g/100g		
	MgO	[1309-48-4]	35,21 ± 0,18	g/100g		
	Al ₂ O ₃		2,9 ± 0,08	g/100g		
	SiO ₂		39,43 ± 0,15	g/100g		
	P ₂ O ₅		0,04 ± 0,02	g/100g		
	K ₂ O		0,02 ± 0,01	g/100g		
	CaO		1,2 ± 0,03	g/100g		
	TiO ₂		0,11 ± 0,01	g/100g		
	MnO		0,12 ± 0,01	g/100g		
	Fe ₂ O ₃ (T)		8,34 ± 0,1	g/100g		
	Lithium (Li)	[7439-93-2]	27 ± 3	g/100g		
	Boron (B)	[7440-42-8]	140 ± 12	g/100g		
	Chlorine (Cl)	[7782-50-5]	800 ± 200	g/100g		
	Scandium (Sc)	[7440-20-2]	13 ± 0,7	g/100g		
	Vanadium (V)	[7440-62-2]	75 ± 9	g/100g		
	Chromium (Cr)	[7440-47-3]	2300 ± 100	g/100g		
	Cobalt (Co)	[7440-48-4]	100 ± 12	g/100g		
	Nickel (Ni)	[7440-02-0]	2000 ± 80	g/100g		
	Copper (Cu)	[7440-50-8]	28 ± 3	g/100g		
	Zinc (Zn)	[7440-66-6]	85 ± 7	g/100g		
	Gallium (Ga)	[7440-55-3]	3 ± 0,5	g/100g		
	Arsenic (As)	[7440-38-2]	10 ± 2	g/100g		
	Rubidium (Rb)	[7440-17-7]	4 ± 2	g/100g		

Strontium (Sr)	[7440-24-6]	9 ± 1,85	g/100g
Yttrium (Y)	[7440-65-5]	2,5 ± 0,2	g/100g
Zirconium (Zr)	[7440-67-7]	4 ± 1	g/100g
Molybdenum (Mo)	[7439-98-7]	0,55 ± 0,1	g/100g
Caesium (Cs)	[7440-46-2]	10 ± 0,9	g/100g
Barium (Ba)	[7440-39-3]	27 ± 3	g/100g
Lanthanum (La)	[7439-91-0]	0,35 ± 0,07	g/100g
Cerium (Ce)	[7440-45-1]	0,8 ± 0,1	g/100g
Praseodymium (Pr)	[7440-10-0]	0,12 ± 0,01	g/100g
Neodymium (Nd)	[7440-00-8]	0,6 ± 0,04	g/100g
Samarium (Sm)	[7440-19-9]	0,2 ± 0,01	g/100g
Europium (Eu)	[7440-53-1]	0,08 ± 0,01	g/100g
Gadolinium (Gd)	[7440-54-2]	0,3 ± 0,03	g/100g
Terbium (Tb)	[7440-27-9]	0,06 ± 0,01	g/100g
Dysprosium (Dy)	[7429-91-6]	0,38 ± 0,03	g/100g
Holmium (Ho)	[7440-60-0]	0,09 ± 0,01	g/100g
Erbium (Er)	[7440-52-0]	0,28 ± 0,02	g/100g
Thulium (Tm)	[7440-30-4]	0,045 ± 0,01	g/100g
Ytterbium (Yb)	[7440-64-4]	0,28 ± 0,02	g/100g
Lutetium (Lu)	[7439-94-3]	0,045 ± 0,005	g/100g
Tantalum (Ta)	[7440-25-7]	0,02 ± 0,005	g/100g
Tungsten (W)	[7440-33-7]	20 ± 7	g/100g
Lead (Pb)	[7439-92-1]	13 ± 3	g/100g