

Blank/lithochem/low-level, Matrix: basalt, Mineralisation Style: barren

Art. ID OREAS-24P-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	7,66	%	Borate Fus ion XRF	
	Calcium (Ca)	[7440-70-2]	6,07	%	Borate Fus ion XRF	
	Chromium (Cr)	[7440-47-3]	0,025	%	Borate Fus ion XRF	
	Iron (Fe)	[7439-89-6]	7,97	%	Borate Fus ion XRF	
	Potassium (K)	[7440-09-7]	0,7	%	Borate Fus ion XRF	
	Magnesium (Mg)	[7439-95-4]	4,13	%	Borate Fus ion XRF	
	Manganese (Mn)	[7439-96-5]	0,11	%	Borate Fus ion XRF	
	Sodium (Na)	[7440-23-5]	2,31	%	Borate Fus ion XRF	
	Phosphorus (P)	[7723-14-0]	0,136	%	Borate Fus ion XRF	
	Silicon (Si)	[7440-21-3]	24,2	%	Borate Fus ion XRF	
	Titanium (Ti)	[7440-32-6]	1,1	%	Borate Fus ion XRF	
	Loss on Ignition (L.O.I) (1000 °C)		0,61	%	Thermograv imetry	
	Carbon (C)	[7440-44-0]	0,07	%	Infrared C ombustion	
	Sulfur (S)	[7704-34-9]	0,013	%	Infrared C ombustion	