

Au <1 ppm, Matrix: quartz conglomerate, Mineralisation Style: modified paleoplacer

Art. ID OREAS-293-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium(III) oxide (Al ₂ O ₃)		3,97	%	Borate Fusion XRF	
	Calcium oxide (CaO)	[1305-78-8]	0,701	%	Borate Fusion XRF	
	Iron (III) oxide (Fe ₂ O ₃)		1,4	%	Borate Fusion XRF	
	Potassium oxide (K ₂ O)		0,903	%	Borate Fusion XRF	
	Magnesium oxide (MgO)	[1309-48-4]	0,338	%	Borate Fusion XRF	
	Manganese oxide (MnO)		0,015	%	Borate Fusion XRF	
	Sodium oxide (Na ₂ O)	[1313-59-3]	0,711	%	Borate Fusion XRF	
	Phosphorus(V) oxide (P ₂ O ₅)		0,053	%	Borate Fusion XRF	
	Sulfur (S)	[7704-34-9]	0,04	%	Borate Fusion XRF	
	Silicon dioxide (SiO ₂)	[7631-86-9]	91,15	%	Borate Fusion XRF	
	Titanium dioxide (TiO ₂)	[13463-67-7]	0,185	%	Borate Fusion XRF	
	Loss on Ignition (L.O.I.) (1000 °C)		0,241	%	Thermogravimetry	
	Aluminium (Al)	[7429-90-5]	2,07	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,506	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	0,973	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	0,742	%	4-Acid Digestion	

					estion
Magnesium (Mg)	[7439-95-4]	0,201	%		4-Acid Dig
					estion
Manganese (Mn)	[7439-96-5]	0,01	%		4-Acid Dig
					estion
Sodium (Na)	[7440-23-5]	0,526	%		4-Acid Dig
					estion
Phosphorus (P)	[7723-14-0]	0,022	%		4-Acid Dig
					estion
Sulfur (S)	[7704-34-9]	0,04	%		4-Acid Dig
					estion
Titanium (Ti)	[7440-32-6]	0,109	%		4-Acid Dig
					estion
Sulfur (S)	[7704-34-9]	0,038	%		Infrared C
					ombustion