

Au >1 ppm, Matrix: quartz conglomerate, Mineralisation Style: modified paleoplacer

Art. ID OREAS-296-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium(III) oxide (Al ₂ O ₃)		3,65	%	Borate Fus ion XRF	
	Calcium oxide (CaO)	[1305-78-8]	0,666	%	Borate Fus ion XRF	
	Iron (III) oxide (Fe ₂ O ₃)		1,91	%	Borate Fus ion XRF	
	Potassium oxide (K ₂ O)		0,83	%	Borate Fus ion XRF	
	Magnesium oxide (MgO)	[1309-48-4]	0,396	%	Borate Fus ion XRF	
	Manganese oxide (MnO)		0,019	%	Borate Fus ion XRF	
	Sodium oxide (Na ₂ O)	[1313-59-3]	0,569	%	Borate Fus ion XRF	
	Phosphorus(V) oxide (P ₂ O ₅)		0,045	%	Borate Fus ion XRF	
	Sulfur (S)	[7704-34-9]	0,237	%	Borate Fus ion XRF	
	Silicon dioxide (SiO ₂)	[7631-86-9]	90,78	%	Borate Fus ion XRF	
	Titanium dioxide (TiO ₂)	[13463-67-7]	0,184	%	Borate Fus ion XRF	
	Loss on Ignition (L.O.I.) (1000 °C)		0,484	%	Thermogravimetry	
	Aluminium (Al)	[7429-90-5]	1,92	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,482	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	1,33	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	0,685	%	4-Acid Digestion	

					estion
Magnesium (Mg)	[7439-95-4]	0,239	%	4-Acid Dig	estion
Manganese (Mn)	[7439-96-5]	0,013	%	4-Acid Dig	estion
Sodium (Na)	[7440-23-5]	0,419	%	4-Acid Dig	estion
Phosphorus (P)	[7723-14-0]	0,019	%	4-Acid Dig	estion
Sulfur (S)	[7704-34-9]	0,249	%	4-Acid Dig	estion
Titanium (Ti)	[7440-32-6]	0,105	%	4-Acid Dig	estion
Sulfur (S)	[7704-34-9]	0,238	%	Infrared C	ombustion