

Zn-Pb-Ag sulphide ore, Concentrates, Matrix: sulphide, Mineralisation Style: Broken Hill Type

Art. ID OREAS-353-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Lead (Pb)	[7439-92-1]	61,26	%	Classical Wet Chemis try	
	Zinc (Zn)	[7440-66-6]	4,13	%	4-Acid Dig estion	
	Aluminium (Al)	[7429-90-5]	0,204	%	4-Acid Dig estion	
	Calcium (Ca)	[7440-70-2]	0,236	%	4-Acid Dig estion	
	Copper (Cu)	[7440-50-8]	0,312	%	4-Acid Dig estion	
	Iron (Fe)	[7439-89-6]	5,35	%	4-Acid Dig estion	
	Potassium (K)	[7440-09-7]	0,045	%	4-Acid Dig estion	
	Magnesium (Mg)	[7439-95-4]	0,685	%	4-Acid Dig estion	
	Manganese (Mn)	[7439-96-5]	0,184	%	4-Acid Dig estion	
	Sodium (Na)	[7440-23-5]	0,028	%	4-Acid Dig estion	
	Phosphorus (P)	[7723-14-0]	0,024	%	4-Acid Dig estion	
	Sulfur (S)	[7704-34-9]	15,13	%	4-Acid Dig estion	
	Titanium (Ti)	[7440-32-6]	0,013	%	4-Acid Dig estion	
	Aluminium (Al)	[7429-90-5]	0,206	%	Peroxide F usion ICP	
	Calcium (Ca)	[7440-70-2]	0,255	%	Peroxide F	

					usion ICP
Iron (Fe)	[7439-89-6]	5,44	%	Peroxide F	usion ICP
Magnesium (Mg)	[7439-95-4]	0,704	%	Peroxide F	usion ICP
Manganese (Mn)	[7439-96-5]	0,186	%	Peroxide F	usion ICP
Sulfur (S)	[7704-34-9]	16,08	%	Peroxide F	usion ICP
Silicon dioxide (SiO ₂)	[7631-86-9]	5,14	%	Peroxide F	usion ICP
Zinc (Zn)	[7440-66-6]	4,14	%	Peroxide F	usion ICP
Carbon (C)	[7440-44-0]	0,766	%	Infrared C	ombustion
Sulfur (S)	[7704-34-9]	15,13	%	Infrared C	ombustion