

*****sold out*** Au <1 ppm, Au-Cu ore, Au-Ag ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal**

Art. ID OREAS-600b-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Sulfur (S)	[7704-34-9]	0,299	%	Infrared C ombustion	
	Aluminium (Al)	[7429-90-5]	7,58	%	4-Acid Dig estion	
	Calcium (Ca)	[7440-70-2]	1,26	%	4-Acid Dig estion	
	Iron (Fe)	[7439-89-6]	2,54	%	4-Acid Dig estion	
	Potassium (K)	[7440-09-7]	3,03	%	4-Acid Dig estion	
	Sodium (Na)	[7440-23-5]	2,76	%	4-Acid Dig estion	
	Sulfur (S)	[7704-34-9]	0,308	%	4-Acid Dig estion	
	Titanium (Ti)	[7440-32-6]	0,12	%	4-Acid Dig estion	
	Aluminium (Al)	[7429-90-5]	0,59	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,817	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	2,05	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,273	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,085	%	Aqua Regia Digestion	
	Sulfur (S)	[7704-34-9]	0,251	%	Aqua Regia Digestion	