

**Au-Ag ore, Au <1 ppm, Au-Cu ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal**

Art. ID                      OREAS-601b-X  
Unit                         on request  
Deliverydetails            No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,101	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	1,49	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	6,63	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,887	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	2,29	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	2,41	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	1,9	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	1,5	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,135	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	0,63	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,578	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	0,101	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	1,94	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,246	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,067	%	Aqua Regia Digestion	

Sulfur (S)

[7704-34-9]

0,807

%

Aqua Regia

Digestion