

Au-Cu ore, Au >1 ppm, Au-Ag ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal

Art. ID OREAS-602b-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,496	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	2,15	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	5,38	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,655	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	2,52	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	1,78	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	1,4	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	2,13	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,149	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	0,546	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,418	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	0,495	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	2,26	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,182	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,052	%	Aqua Regia Digestion	

Sulfur (S)

[7704-34-9]

1,56

%

Aqua Regia

Digestion