

Au-Cu ore, Au >1 ppm, Au-Ag ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal

Art. ID OREAS-604b-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	2,12	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	4,83	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	6,55	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,704	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	4,25	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	1,88	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	1,4	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	4,76	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,166	%	4-Acid Digestion	
	Zinc (Zn)	[7440-66-6]	0,117	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	0,807	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,421	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	2,12	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	4,01	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,224	%	Aqua Regia Digestion	

Sodium (Na)	[7440-23-5]	0,058	%	Aqua Regia Digestion
Sulfur (S)	[7704-34-9]	4,07	%	Aqua Regia Digestion
Zinc (Zn)	[7440-66-6]	0,112	%	Aqua Regia Digestion