

**\*\*\*sold out\*\*\* Au-Ag ore, Au-Cu ore, Au >1 ppm, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal**

Art. ID OREAS-605b-X  
Unit 10g  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	5,03	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	10,29	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	6,26	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,423	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	7,14	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	1,2	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	0,527	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	9,96	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,212	%	4-Acid Digestion	
	Zinc (Zn)	[7440-66-6]	0,24	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	1,15	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,197	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	4,96	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	6,99	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,247	%	Aqua Regia Digestion	

Sodium (Na)	[7440-23-5]	0,051	%	Aqua Regia Digestion
Sulfur (S)	[7704-34-9]	9,21	%	Aqua Regia Digestion
Zinc (Zn)	[7440-66-6]	0,232	%	Aqua Regia Digestion