

Au <1 ppm, Au-Ag ore, Au-Cu ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal

Art. ID OREAS-607-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Sulfur (S)	[7704-34-9]	0,981	%	Infrared C ombustion	
	Aluminium (Al)	[7429-90-5]	6,8	%	4-Acid Dig estion	
	Calcium (Ca)	[7440-70-2]	0,494	%	4-Acid Dig estion	
	Iron (Fe)	[7439-89-6]	1,71	%	4-Acid Dig estion	
	Potassium (K)	[7440-09-7]	3,06	%	4-Acid Dig estion	
	Sodium (Na)	[7440-23-5]	1,61	%	4-Acid Dig estion	
	Sulfur (S)	[7704-34-9]	0,974	%	4-Acid Dig estion	
	Titanium (Ti)	[7440-32-6]	0,166	%	4-Acid Dig estion	
	Aluminium (Al)	[7429-90-5]	0,903	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,222	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	1,48	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,279	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,068	%	Aqua Regia Digestion	
	Sulfur (S)	[7704-34-9]	0,505	%	Aqua Regia Digestion	