

Au >1 ppm, Au-Ag ore, Au-Cu ore, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal

Art. ID OREAS-609-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,495	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	3,47	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	6,39	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,294	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	2,09	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	2,25	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	0,934	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	3,43	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,161	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	0,889	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,15	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	0,497	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	1,97	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,236	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,051	%	Aqua Regia Digestion	

Sulfur (S)

[7704-34-9]

1,95

%

Aqua Regia

Digestion