

Au-Ag ore, Au-Cu ore, Au >1 ppm, Matrix: rhyodacite, Mineralisation Style: high sulphidation epithermal

Art. ID OREAS-610-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,971	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	4,12	%	Infrared Combustion	
	Aluminium (Al)	[7429-90-5]	5,99	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	0,241	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	2,37	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	1,98	%	4-Acid Digestion	
	Sodium (Na)	[7440-23-5]	0,82	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	4,07	%	4-Acid Digestion	
	Titanium (Ti)	[7440-32-6]	0,167	%	4-Acid Digestion	
	Aluminium (Al)	[7429-90-5]	0,847	%	Aqua Regia Digestion	
	Calcium (Ca)	[7440-70-2]	0,12	%	Aqua Regia Digestion	
	Copper (Cu)	[7440-50-8]	0,972	%	Aqua Regia Digestion	
	Iron (Fe)	[7439-89-6]	2,27	%	Aqua Regia Digestion	
	Potassium (K)	[7440-09-7]	0,213	%	Aqua Regia Digestion	
	Sodium (Na)	[7440-23-5]	0,049	%	Aqua Regia Digestion	

Sulfur (S)

[7704-34-9]

2,65

%

Aqua Regia

Digestion