

Au-Pd-Pt (PGE) ore, Ni-Cu-PGE, Au <1 ppm, Matrix: gabbronorite, Mineralisation Style: magmatic Ni-Cu-PGE

Art. ID OREAS-680-X
Unit on request
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	7,19	%	Peroxide Fusion ICP	
	Calcium (Ca)	[7440-70-2]	5,8	%	Peroxide Fusion ICP	
	Copper (Cu)	[7440-50-8]	0,904	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	11,93	%	Peroxide Fusion ICP	
	Potassium (K)	[7440-09-7]	1,29	%	Peroxide Fusion ICP	
	Magnesium (Mg)	[7439-95-4]	3,71	%	Peroxide Fusion ICP	
	Manganese (Mn)	[7439-96-5]	0,124	%	Peroxide Fusion ICP	
	Nickel (Ni)	[7440-02-0]	2,15	%	Peroxide Fusion ICP	
	Phosphorus (P)	[7723-14-0]	0,122	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	5,14	%	Peroxide Fusion ICP	
	Silicon (Si)	[7440-21-3]	20,62	%	Peroxide Fusion ICP	
	Titanium (Ti)	[7440-32-6]	0,523	%	Peroxide Fusion ICP	
	Aluminium (Al)	[7429-90-5]	7,13	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	5,58	%	4-Acid Digestion	
	Copper (Cu)	[7440-50-8]	0,897	%	4-Acid Digestion	

Iron (Fe)	[7439-89-6]	11,68	%	4-Acid Digestion
Potassium (K)	[7440-09-7]	1,24	%	4-Acid Digestion
Magnesium (Mg)	[7439-95-4]	3,58	%	4-Acid Digestion
Manganese (Mn)	[7439-96-5]	0,122	%	4-Acid Digestion
Sodium (Na)	[7440-23-5]	1,45	%	4-Acid Digestion
Nickel (Ni)	[7440-02-0]	2,12	%	4-Acid Digestion
Phosphorus (P)	[7723-14-0]	0,126	%	4-Acid Digestion
Sulfur (S)	[7704-34-9]	4,98	%	4-Acid Digestion
Titanium (Ti)	[7440-32-6]	0,513	%	4-Acid Digestion