

Au-Pd-Pt (PGE) ore, Au <1 ppm, Matrix: gabbronorite, Mineralisation Style: magmatic PGE

Art. ID OREAS-682-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	8,87	%	Peroxide Fusion ICP	
	Calcium (Ca)	[7440-70-2]	6,62	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	6,94	%	Peroxide Fusion ICP	
	Potassium (K)	[7440-09-7]	1,18	%	Peroxide Fusion ICP	
	Magnesium (Mg)	[7439-95-4]	4,95	%	Peroxide Fusion ICP	
	Manganese (Mn)	[7439-96-5]	0,12	%	Peroxide Fusion ICP	
	Phosphorus (P)	[7723-14-0]	0,123	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	0,111	%	Peroxide Fusion ICP	
	Silicon (Si)	[7440-21-3]	23,96	%	Peroxide Fusion ICP	
	Titanium (Ti)	[7440-32-6]	0,511	%	Peroxide Fusion ICP	
	Aluminium (Al)	[7429-90-5]	8,84	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	6,4	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	6,78	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	1,18	%	4-Acid Digestion	
	Magnesium (Mg)	[7439-95-4]	4,86	%	4-Acid Digestion	

Manganese (Mn)	[7439-96-5]	0,116	%	4-Acid Digestion
Sodium (Na)	[7440-23-5]	1,6	%	4-Acid Digestion
Phosphorus (P)	[7723-14-0]	0,122	%	4-Acid Digestion
Sulfur (S)	[7704-34-9]	0,114	%	4-Acid Digestion
Titanium (Ti)	[7440-32-6]	0,503	%	4-Acid Digestion