

**Au-Pd-Pt (PGE) ore, Au <1 ppm, Matrix: pyroxenite, Mineralisation Style: magmatic PGE**

Art. ID                      OREAS-683-X  
Unit                         on request  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	7,24	%	Peroxide Fusion ICP	
	Calcium (Ca)	[7440-70-2]	5,32	%	Peroxide Fusion ICP	
	Chromium (Cr)	[7440-47-3]	0,994	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	7,46	%	Peroxide Fusion ICP	
	Potassium (K)	[7440-09-7]	0,506	%	Peroxide Fusion ICP	
	Magnesium (Mg)	[7439-95-4]	8,65	%	Peroxide Fusion ICP	
	Manganese (Mn)	[7439-96-5]	0,124	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	0,194	%	Peroxide Fusion ICP	
	Silicon (Si)	[7440-21-3]	22,87	%	Peroxide Fusion ICP	
	Titanium (Ti)	[7440-32-6]	0,27	%	Peroxide Fusion ICP	
	Aluminium (Al)	[7429-90-5]	7,15	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	5,23	%	4-Acid Digestion	
	Chromium (Cr)	[7440-47-3]	0,771	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	7,32	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	0,507	%	4-Acid Digestion	
	Magnesium (Mg)	[7439-95-4]	8,63	%	4-Acid Digestion	

					estion
Manganese (Mn)	[7439-96-5]	0,12	%	4-Acid Dig	estion
Sodium (Na)	[7440-23-5]	1,03	%	4-Acid Dig	estion
Phosphorus (P)	[7723-14-0]	0,05	%	4-Acid Dig	estion
Sulfur (S)	[7704-34-9]	0,205	%	4-Acid Dig	estion
Titanium (Ti)	[7440-32-6]	0,263	%	4-Acid Dig	estion