

**Au-Pd-Pt (PGE) ore, Au <1 ppm, Matrix: pyroxenite, Mineralisation Style: magmatic PGE**

Art. ID                    OREAS-684-X  
Unit                      on request  
Deliverydetails        No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Aluminium (Al)	[7429-90-5]	6,02	%	Peroxide Fusion ICP	
	Calcium (Ca)	[7440-70-2]	4,56	%	Peroxide Fusion ICP	
	Chromium (Cr)	[7440-47-3]	1,36	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	8	%	Peroxide Fusion ICP	
	Potassium (K)	[7440-09-7]	0,19	%	Peroxide Fusion ICP	
	Magnesium (Mg)	[7439-95-4]	10,85	%	Peroxide Fusion ICP	
	Manganese (Mn)	[7439-96-5]	0,129	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	0,455	%	Peroxide Fusion ICP	
	Silicon (Si)	[7440-21-3]	22,42	%	Peroxide Fusion ICP	
	Titanium (Ti)	[7440-32-6]	0,144	%	Peroxide Fusion ICP	
	Aluminium (Al)	[7429-90-5]	5,96	%	4-Acid Digestion	
	Calcium (Ca)	[7440-70-2]	4,44	%	4-Acid Digestion	
	Chromium (Cr)	[7440-47-3]	1,04	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	7,87	%	4-Acid Digestion	
	Potassium (K)	[7440-09-7]	0,152	%	4-Acid Digestion	
	Magnesium (Mg)	[7439-95-4]	10,78	%	4-Acid Digestion	

					estion
Manganese (Mn)	[7439-96-5]	0,127	%	4-Acid Dig	estion
Sodium (Na)	[7440-23-5]	0,675	%	4-Acid Dig	estion
Phosphorus (P)	[7723-14-0]	0,012	%	4-Acid Dig	estion
Sulfur (S)	[7704-34-9]	0,459	%	4-Acid Dig	estion
Titanium (Ti)	[7440-32-6]	0,138	%	4-Acid Dig	estion