

Ni sulphide ore, Matrix: mineralised ultramafic, Mineralisation Style: komatiite-hosted nickel sulphide

Art. ID OREAS-73a-X
Unit on request
Deliverydetails No Dangerous Good

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Nickel (Ni)	[7440-02-0]	1,41	%	4-Acid Digestion	
	Aluminium(III) oxide (Al ₂ O ₃)		2,38	%	Borate / Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	9,24	%	Borate / Peroxide Fusion ICP	
	Magnesium oxide (MgO)	[1309-48-4]	32,5	%	Borate / Peroxide Fusion ICP	
	Nickel (Ni)	[7440-02-0]	1,44	%	Borate / Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	3,02	%	Borate / Peroxide Fusion ICP	
	Silicon dioxide (SiO ₂)	[7631-86-9]	36,4	%	Borate / Peroxide Fusion ICP	
	Aluminium(III) oxide (Al ₂ O ₃)		2,42	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	9,2	%	4-Acid Digestion	
	Magnesium oxide (MgO)	[1309-48-4]	32,6	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	3,31	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	3,16	%	Infrared Combustion	

