

Barren (coarse) drill chips, CRM, Matrix: basalt, Mineralisation Style: barren

Art. ID OREAS-26b-200KG
Unit 200 kg
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--|--------------|---------------------|------|-----------------------|--------|
| | Gold (Au) | [7440-57-5] | < 1 | ppb | Pb Fire As say | |
| | Copper (Cu) | [7440-50-8] | 0,00437 | % | 4-Acid Dig estion | |
| | Iron(II) oxide (FeO) | | 10,35 | % | Borate Fus ion XRF | |
| | Al ₂ O ₃ | | 14,39 | % | Borate Fus ion XRF | |
| | CaO | | 8,57 | % | Borate Fus ion XRF | |
| | Cr ₂ O ₃ | | 0,0524 | % | Borate Fus ion XRF | |
| | Potassium oxide (K ₂ O) | | 0,833 | % | Borate Fus ion XRF | |
| | Magnesium oxide (MgO) | [1309-48-4] | 7,38 | % | Borate Fus ion XRF | |
| | Manganese oxide (MnO) | | 0,149 | % | Borate Fus ion XRF | |
| | Sodium oxide (Na ₂ O) | [1313-59-3] | 3,16 | % | Borate Fus ion XRF | |
| | Phosphorous(V) oxide (P 2O ₅) | | 0,334 | % | Borate Fus ion XRF | |
| | Silicon dioxide (SiO ₂) | [7631-86-9] | 51,2 | % | Borate Fus ion XRF | |
| | Titanium dioxide (TiO ₂) | [13463-67-7] | 1,85 | % | Borate Fus ion XRF | |
| | Loss on Ignition (L.O.I) (1000 °C) | | 0,535 | % | Thermograv imetry | |
| | Aluminium (Al) | [7429-90-5] | 7,47 | % | 4-Acid Dig estion | |
| | Barium (Ba) | [7440-39-3] | 0,0255 | % | 4-Acid Dig | |

| | | | | | |
|-----------------|-------------|-----------|---|------------|--------|
| | | | | | estion |
| Beryllium (Be) | [7440-41-7] | 0,000099 | % | 4-Acid Dig | estion |
| Calcium (Ca) | [7440-70-2] | 5,92 | % | 4-Acid Dig | estion |
| Cerium (Ce) | [7440-45-1] | 0,00363 | % | 4-Acid Dig | estion |
| Cobalt (Co) | [7440-48-4] | 0,00444 | % | 4-Acid Dig | estion |
| Chromium (Cr) | [7440-47-3] | 0,0293 | % | 4-Acid Dig | estion |
| Cesium (Cs) | | 0,000067 | % | 4-Acid Dig | estion |
| Iron (Fe) | [7439-89-6] | 7,74 | % | 4-Acid Dig | estion |
| Gallium (Ga) | [7440-55-3] | 0,00202 | % | 4-Acid Dig | estion |
| Hafnium (Hf) | [7440-58-6] | 0,00035 | % | 4-Acid Dig | estion |
| Indium (In) | [7440-74-6] | 0,0000061 | % | 4-Acid Dig | estion |
| Potassium (K) | [7440-09-7] | 0,679 | % | 4-Acid Dig | estion |
| Lanthanum (La) | [7439-91-0] | 0,00174 | % | 4-Acid Dig | estion |
| Lithium (Li) | [7439-93-2] | 0,000638 | % | 4-Acid Dig | estion |
| Magnesium (Mg) | [7439-95-4] | 4,3 | % | 4-Acid Dig | estion |
| Manganese (Mn) | [7439-96-5] | 0,11 | % | 4-Acid Dig | estion |
| Molybdenum (Mo) | [7439-98-7] | 0,000143 | % | 4-Acid Dig | estion |
| Sodium (Na) | [7440-23-5] | 2,34 | % | 4-Acid Dig | estion |
| Niobium (Nb) | [7440-03-1] | 0,00213 | % | 4-Acid Dig | estion |
| Nickel (Ni) | [7440-02-0] | 0,0149 | % | 4-Acid Dig | estion |

| | | | | | |
|----------------|-------------|-----------|---|------------|--------|
| | | | | | estion |
| Phosphorus (P) | [7723-14-0] | 0,141 | % | 4-Acid Dig | estion |
| Lead (Pb) | [7439-92-1] | 0,000281 | % | 4-Acid Dig | estion |
| Rubidium (Rb) | [7440-17-7] | 0,00201 | % | 4-Acid Dig | estion |
| Sulfur (S) | [7704-34-9] | 0,01 | % | 4-Acid Dig | estion |
| Scandium (Sc) | [7440-20-2] | 0,00196 | % | 4-Acid Dig | estion |
| Tin (Sn) | [7440-31-5] | 0,000183 | % | 4-Acid Dig | estion |
| Strontium (Sr) | [7440-24-6] | 0,0412 | % | 4-Acid Dig | estion |
| Tantalum (Ta) | [7440-25-7] | 0,000136 | % | 4-Acid Dig | estion |
| Thorium (Th) | [7440-29-1] | 0,00026 | % | 4-Acid Dig | estion |
| Titanium (Ti) | [7440-32-6] | 1,06 | % | 4-Acid Dig | estion |
| Thallium (Tl) | [7440-28-0] | 0,0000059 | % | 4-Acid Dig | estion |
| Uranium (U) | [7440-61-1] | 0,000065 | % | 4-Acid Dig | estion |
| Vanadium (V) | [7440-62-2] | 0,0155 | % | 4-Acid Dig | estion |
| Tungsten (W) | [7440-33-7] | 0,00005 | % | 4-Acid Dig | estion |
| Yttrium (Y) | [7440-65-5] | 0,00212 | % | 4-Acid Dig | estion |
| Zinc (Zn) | [7440-66-6] | 0,011 | % | 4-Acid Dig | estion |
| Zirconium (Zr) | [7440-67-7] | 0,0135 | % | 4-Acid Dig | estion |