

**Cu ore, Blank/Litho-geochem, CRM, Matrix: shale / siliceous dolomite, Mineralisation Style: barren**

Art. ID                    OREAS-160-10G  
Unit                        10 g  
Deliverydetails        No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,0013	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	1,13	%	Peroxide Fusion ICP	
	Cobalt (Co)	[7440-48-4]	0,00028	%	4-Acid Digestion	
	Al <sub>2</sub> O <sub>3</sub>		5,01	%	Peroxide Fusion ICP	
	Magnesium oxide (MgO)	[1309-48-4]	0,64	%	4-Acid Digestion	
	Silicon dioxide (SiO <sub>2</sub> )	[7631-86-9]	88,7	%	Peroxide Fusion ICP	
	Silver (Ag)	[7440-22-4]	< 0,00002	%	4-Acid Digestion	
	Silver (Ag)	[7440-22-4]	< 0,0002	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	0,029	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	0,04	%	Peroxide Fusion ICP	
	Zinc (Zn)	[7440-66-6]	0,0007	%	4-Acid Digestion	
	Magnesium oxide (MgO)	[1309-48-4]	0,62	%	Peroxide Fusion ICP	
	Lead (Pb)	[7439-92-1]	0,0007	%	Peroxide Fusion ICP	
	Lead (Pb)	[7439-92-1]	0,00066	%	4-Acid Digestion	
	Iron (Fe)	[7439-89-6]	1,15	%	4-Acid Digestion	

Cobalt (Co)	[7440-48-4]	< 0,0008	%	Peroxide F usion ICP
Copper (Cu)	[7440-50-8]	< 0,02	%	Peroxide F usion ICP
CaO		0,15	%	Peroxide F usion ICP
CaO		0,146	%	4-Acid Dig estion
Al <sub>2</sub> O <sub>3</sub>		5,04	%	4-Acid Dig estion
Zinc (Zn)	[7440-66-6]	< 0,003	%	Peroxide F usion ICP