

**Cu ore, CRM, Matrix: siliceous dolomite, Mineralisation Style: sediment hosted**

Art. ID OREAS-162-10G  
Unit 10 g  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	0,761	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	8,63	%	Peroxide Fusion ICP	
	Cobalt (Co)	[7440-48-4]	0,0631	%	4-Acid Digestion	
	Magnesium oxide (MgO)	[1309-48-4]	9,17	%	4-Acid Digestion	
	Silicon dioxide (SiO <sub>2</sub> )	[7631-86-9]	40,4	%	Peroxide Fusion ICP	
	Silver (Ag)	[7440-22-4]	0,00035	%	4-Acid Digestion	
	Al <sub>2</sub> O <sub>3</sub>		1,64	%	Peroxide Fusion ICP	
	Silver (Ag)	[7440-22-4]	< 0,001	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	4,38	%	4-Acid Digestion	
	Sulfur (S)	[7704-34-9]	4,4	%	Peroxide Fusion ICP	
	Zinc (Zn)	[7440-66-6]	< 0,005	%	Peroxide Fusion ICP	
	Magnesium oxide (MgO)	[1309-48-4]	9,04	%	Peroxide Fusion ICP	
	Lead (Pb)	[7439-92-1]	0,034	%	4-Acid Digestion	
	Lead (Pb)	[7439-92-1]	0,032	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	8,57	%	4-Acid Digestion	
	Copper (Cu)	[7440-50-8]	0,772	%	4-Acid Digestion	

					estion
Cobalt (Co)	[7440-48-4]	0,066	%		Peroxide F usion ICP
CaO		13,2	%		4-Acid Dig estion
CaO		13,1	%		Peroxide F usion ICP
Al <sub>2</sub> O <sub>3</sub>		1,7	%		4-Acid Dig estion
Zinc (Zn)	[7440-66-6]	0,0026	%		4-Acid Dig estion