

**Cu ore, CRM, Matrix: siliceous dolomite, Mineralisation Style: sediment hosted**

Art. ID OREAS-163-10G  
Unit 10 g  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	1,71	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	11,1	%	Peroxide Fusion ICP	
	Cobalt (Co)	[7440-48-4]	0,023	%	4-Acid Digestion	
	Magnesium oxide (MgO)	[1309-48-4]	5,42	%	4-Acid Digestion	
	Silicon dioxide (SiO <sub>2</sub> )	[7631-86-9]	63,4	%	Peroxide Fusion ICP	
	Silver (Ag)	[7440-22-4]	0,00043	%	4-Acid Digestion	
	Al <sub>2</sub> O <sub>3</sub>		3,16	%	Peroxide Fusion ICP	
	Silver (Ag)	[7440-22-4]	0,0005	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	9,98	%	Peroxide Fusion ICP	
	Sulfur (S)	[7704-34-9]	10,4	%	4-Acid Digestion	
	Zinc (Zn)	[7440-66-6]	0,0102	%	Peroxide Fusion ICP	
	Magnesium oxide (MgO)	[1309-48-4]	5,34	%	Peroxide Fusion ICP	
	Lead (Pb)	[7439-92-1]	0,0492	%	4-Acid Digestion	
	Lead (Pb)	[7439-92-1]	0,0461	%	Peroxide Fusion ICP	
	Iron (Fe)	[7439-89-6]	11,07	%	4-Acid Digestion	
	Copper (Cu)	[7440-50-8]	1,76	%	4-Acid Digestion	

					estion
Cobalt (Co)	[7440-48-4]	0,023	%		Peroxide F usion ICP
CaO		0,92	%		Peroxide F usion ICP
CaO		0,86	%		4-Acid Dig estion
Al <sub>2</sub> O <sub>3</sub>		3,24	%		4-Acid Dig estion
Zinc (Zn)	[7440-66-6]	0,0108	%		4-Acid Dig estion