

Cu ore, CRM, Matrix: siliceous dolomite, Mineralisation Style: sediment hosted

Art. ID OREAS-164-10G
Unit 10 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Copper (Cu)	[7440-50-8]	2,22	%	Peroxide F usion ICP	
	Iron (Fe)	[7439-89-6]	6,88	%	Peroxide F usion ICP	
	Cobalt (Co)	[7440-48-4]	0,0168	%	4-Acid Dig estion	
	Magnesium oxide (MgO)	[1309-48-4]	3,07	%	4-Acid Dig estion	
	Silicon dioxide (SiO ₂)	[7631-86-9]	77,9	%	Peroxide F usion ICP	
	Silver (Ag)	[7440-22-4]	< 0,0005	%	Peroxide F usion ICP	
	Al ₂ O ₃		2,05	%	Peroxide F usion ICP	
	Silver (Ag)	[7440-22-4]	0,000294	%	4-Acid Dig estion	
	Sulfur (S)	[7704-34-9]	5,98	%	Peroxide F usion ICP	
	Sulfur (S)	[7704-34-9]	6,2	%	4-Acid Dig estion	
	Zinc (Zn)	[7440-66-6]	0,0045	%	4-Acid Dig estion	
	Magnesium oxide (MgO)	[1309-48-4]	3,07	%	Peroxide F usion ICP	
	Lead (Pb)	[7439-92-1]	0,0214	%	4-Acid Dig estion	
	Lead (Pb)	[7439-92-1]	0,0199	%	Peroxide F usion ICP	
	Iron (Fe)	[7439-89-6]	6,8	%	4-Acid Dig estion	
	Copper (Cu)	[7440-50-8]	2,25	%	4-Acid Dig	

					estion
Cobalt (Co)	[7440-48-4]	0,0167	%		Peroxide F usion ICP
CaO		0,401	%		Peroxide F usion ICP
CaO		0,393	%		4-Acid Dig estion
Al ₂ O ₃		2,07	%		4-Acid Dig estion
Zinc (Zn)	[7440-66-6]	0,0047	%		Peroxide F usion ICP